

Rapid Recoat Epoxy

PRODUCT DESCRIPTION A two component, high solids, low VOC, epoxy zinc phosphate/micaceous iron oxide primer offering excellent barrier protection, low temperature cure and rapid overcoating properties.

INTENDED USES As a primer for steelwork intended for use in a wide range of environmental conditions including offshore, chemical and petrochemical plants, industrial buildings, pulp and paper mills, power plants and bridges.
 Suitable for overcoating within 7 hours in most climatic conditions hence speeding up production and throughput in fabrication shops.
 Provides quick cure even at low temperatures often encountered in maintenance painting.

PRACTICAL INFORMATION FOR INTERCURE 200HS

Color Sand, Grey, Red

Gloss Level Matte

Volume Solids 80%

Typical Thickness 6-8 mils (150-200 microns) dry equivalent to 7.5-10 mils (188-250 microns) wet

Theoretical Coverage 214 sq.ft/US gallon at 6 mils d.f.t and stated volume solids
 5.30 m²/liter at 150 microns d.f.t and stated volume solids

Practical Coverage Allow appropriate loss factors

Method of Application Airless Spray, Air Spray, Brush, Roller

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
41°F (5°C)	4 hours	10 hours	7 hours	Extended ¹
59°F (15°C)	3 hours	6 hours	4 hours	Extended ¹
77°F (25°C)	2 hours	3 hours	3 hours	Extended ¹
104°F (40°C)	30 minutes	1 hour	1 hour	Extended ¹

¹ See International Protective Coatings Definitions & Abbreviations

REGULATORY DATA **Flash Point (Typical)** Part A 100°F (38°C); Part B 81°F (27°C); Mixed 91°F (33°C)

Product Weight 13.9 lb/gal (1.67 kg/l)

VOC 1.91 lb/gal (230 g/l)
 139 g/kg

EPA Method 24
 EU Solvent Emissions Directive
 (Council Directive 1999/13/EC)

See Product Characteristics section for further details

Rapid Recoat Epoxy

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to SSPC SP6 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Intercure 200HS the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Intercure 200HS is suitable for application to blast cleaned surfaces which were initially to the above standard but have been allowed to deteriorate under good shop conditions for up to 7-10 days. The surface may deteriorate to Sa2 standard but must be free from loose powdery deposits.

A sharp, angular profile of 2-3 mils (50-75µm) should be achieved.

Shop Primed Steel

Weld seams and damaged areas should be blast cleaned to SSPC SP6 or Sa2½ (ISO 8501-1:2007).

If the shop primer shows extensive or widely scattered breakdown overall sweep blasting maybe necessary.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed, it must be used within the working pot life specified.			
	(1)	Agitate Base (Part A) with a power agitator.		
	(2)	Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
Mix Ratio	3 part(s) : 1 part(s) by volume			
Working Pot Life	41°F (5°C) 150 minutes	59°F (15°C) 90 minutes	77°F (25°C) 1 hour	104°F (40°C) 20 minutes
Airless Spray	Recommended	Tip Range 18-23 thou (0.45-0.58 mm) Total output fluid pressure at spray tip not less than 2417 psi (170 kg/cm ²)		
Air Spray (Pressure Pot)	Recommended (5% thinning required)	Gun	DeVilbiss MBC or JGA	
		Air Cap	704 or 765	
		Fluid Tip	E	
Brush	Suitable - Small areas only	Typically 3.0 mils (75 microns) can be achieved		
Roller	Suitable - Small areas only	Typically 3.0 mils (75 microns) can be achieved		
Thinner	International GTA220	Do not thin more than allowed by local environmental legislation		
Cleaner	International GTA220 (or GTA415)			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA415. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA415. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Rapid Recoat Epoxy

PRODUCT CHARACTERISTICS

Intercure 200HS is preferred for use with systems for chemical environments where zinc based materials can be subject to attack in both acidic and alkaline conditions.

Over-application should be avoided as thick films will not be as good a substrate for topcoat adhesion after ageing as those at the specified thickness.

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

This product must only be thinned using recommended International GTA220 thinners. The use of alternative thinners, particularly those containing ketones, can severely inhibit the curing mechanism of the coating.

At low temperatures, it may be necessary to thin Intercure 200HS to enable airless spray application to be performed. Normally 2% thinning (by volume) with International GTA220 will be satisfactory for this purpose.

Intercure 200HS is capable of curing at temperatures below 32°F (0°C). However, this product should not be applied at temperatures below 32°F (0°C) where there is a possibility of ice formation on the substrate.

This product is not available in pale and pastel shades due to a tendency to discolour rapidly. Additionally, in common with all epoxies Intercure 200HS will chalk on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Intercure 200HS is not intended for use as a primer for steelwork which may be subjected to continuous immersion conditions.

Intercure 200HS can also be used as a primer for substrates other than blasted steel, e.g. stainless steel, alloys, etc. Consult International Protective Coatings for further details.

Absolute measured adhesion of topcoats to aged Intercure 200HS is less than that to fresh material, however, it is adequate for the specified end use.

Over-application of Intercure 200HS will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

Excessive over application of material on areas such as poorly prepared welds may result in long term stress cracking and so early failure.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also effect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

Intercure 200HS will normally be applied to suitably prepared steel, e.g. blast cleaned. However, if necessary, application over prefabrication blast primers can be performed. Consult International Protective Coatings for further details.

Recommended topcoats/intermediates are:

Intercure 420HS	Interfine 629HS
Interfine 878	Interfine 979
Intergard 345	Intergard 475HS
Intergard 410	Intergard 740
Interseal 670HS	Interthane 870
Interthane 990	Interzone 1000
Interzone 505	Interzone 954

For other suitable topcoats/intermediates, consult International Protective Coatings.

Rapid Recoat Epoxy

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 liter	15 liter	20 liter	5 liter	5 liter
	4 US gal	3 US gal	5 US gal	1 US gal	1 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
	20 liter	30.5 kg		5.4 kg	
	4 US gal	47.3 lb		8.1 lb	
STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 2/5/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com