

## Epoxy

### PRODUCT DESCRIPTION

A two component, solvent free, heavy duty epoxy tank lining.

### INTENDED USES

For application to steel tank internals to provide corrosion resistance to a range of products including crude oil, white oils and potable water.

When used for potable water tank applications, please review the approval available at [www.nsf.org](http://www.nsf.org) for current listing information.

Meets the applicable health effects criteria of NSF/ANSI/CAN 600 according to the requirements of NSF/ANSI/CAN 61.



Certified to NSF/ANSI/CAN  
Standard 61

### PRACTICAL INFORMATION FOR INTERLINE 975P

<b>Color</b>	Buff, White
<b>Gloss Level</b>	Not applicable
<b>Volume Solids</b>	100%
<b>Typical Thickness</b>	12-24 mils (300-600 microns) dry equivalent to 12-24 mils (300-600 microns) wet 400-1000 microns (16-40 mils) for use as a single coat on tank floors. Thickness is dependent upon application method and specification.
<b>Theoretical Coverage</b>	89 sq.ft/US gallon at 18 mils d.f.t and stated volume solids 2.22 m <sup>2</sup> /liter at 450 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Plural component airless spray

### Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
50°F (10°C)	15 hours	36 hours	36 hours	28 days <sup>1</sup>
59°F (15°C)	12 hours	24 hours	24 hours	28 days <sup>1</sup>
77°F (25°C)	7 hours	16 hours	16 hours	21 days <sup>1</sup>
104°F (40°C)	3 hours	6 hours	6 hours	14 days <sup>1</sup>

<sup>1</sup> The values quoted relate to use within an enclosed tank environment. For situations where UV exposure between coats is likely, maximum overcoating intervals will be shorter. Contact International Protective Coatings for more details.

<b>REGULATORY DATA</b>	<b>Flash Point (Typical)</b>	Part A >214°F (>101°C); Part B >214°F (>101°C); Mixed >214°F (>101°C)
	<b>Product Weight</b>	10.8 lb/gal (1.3 kg/l)
	<b>VOC</b>	0.00 lb/gal (0 g/lit) EPA Method 24

See Product Characteristics section for further details

## Protective Coatings

## Epoxy

### SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Where necessary, remove weld spatter and smooth weld seams and sharp edges. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

#### Steel

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2.5 (ISO 8501-1:2007) or SSPC-SP10. A sharp, angular surface profile of 3-4 mils (75-100 microns) is recommended. Interline 975P must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidized area should be reblasted to the standard specified above. Surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner.

Where end service use, relevant approvals or VOC regulations allow, steel surfaces may be primed with Interline 982 to 0.6-1.0 mils (15-25 microns) dry film thickness before oxidation occurs. Alternatively, the blast standard can be maintained by use of dehumidification.

#### Concrete Surfaces

Refer to International Protective Coatings for specific recommendations.

## APPLICATION

<b>Mixing</b>	The detailed Interline 975P Application Guidelines should be consulted prior to use.			
	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1) Agitate Base (Part A) with a power agitator.			
	(2) Agitate Curing Agent (Part B) with a power agitator.			
	(3) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
<b>Mix Ratio</b>	2 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	50°F (10°C) 90 minutes	59°F (15°C) 80 minutes	77°F (25°C) 55 minutes	104°F (40°C) 35 minutes
<b>Plural component airless spray</b>	Recommended	Consult International Protective Coatings		
<b>Airless Spray</b>	Recommended	Tip Range 21-26 thou (0.53-0.66 mm) Total output fluid pressure at spray tip not less than 3000 psi (211 kg/cm <sup>2</sup> )		
<b>Brush</b>	Suitable	Small areas only		
<b>Roller</b>	Suitable	Small areas only		
<b>Thinner</b>	DO NOT THIN			
<b>Cleaner</b>	International GTA853 (or GTA415)			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA853. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA853. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

## Epoxy

### PRODUCT CHARACTERISTICS

The detailed Interline 975P Application Guidelines should be consulted prior to use.

Exact specification for total dry film thickness and number of coats will be dependent upon the service end use requirements. Consult International Protective Coatings for specific advice regarding tank lining applications.

Interline 975P is also suitable for application to suitably primed concrete tanks or bunds, where the end service use is not for potable water.

Apply by plural component airless spray or standard airless spray. Application by other methods, e.g. brush or roller, may require more than one coat and is suggested for small areas only or initial stripe coating. Stripe coating is an essential part of good working practice and as such should form part of any lining specification. For heavily pitted or porous steel, spray apply approximately 50% of the required film thickness and follow immediately with a short nap roller or squeegee to work material into the bottom of pitted areas.

Surface temperature must always be a minimum of 5°F (3°C) above dew point. Do not apply at steel temperatures below 50°F (10°C).

The climatic conditions within the tank must be controlled as recommended in the Interline 975P Application Guidelines. The relative humidity within the confines of the tank should be controlled using dehumidification equipment. Where such equipment is not available, a single coat application technique should be employed to avoid intercoat adhesion problems.

Where multi-coat systems are to be used, optimum intercoat adhesion is best achieved by keeping the overcoating interval as short as possible.

Exposure to unacceptably low temperatures and/or high humidities during, or immediately after, application may result in incomplete cure and surface contamination that could jeopardize subsequent intercoat adhesion.

After the last coat has cured hard, the coating system dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the average total applied system thickness. The coating system should be free of all pinholes or other holidays and verified using a suitable method as recommended in the Interline 975P Application Guidelines. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service. Consult International Protective Coatings Interline 975P Application Guidelines for detailed repair procedures.

#### Return to Service

The following minimum cure times are recommended for Interline 975P to achieve its full chemical resistance properties.

<u>Temperature</u>	<u>Cure Schedule</u>
45°F (7°C)	21 days
50°F (10°C)	14 days
59°F (15°C)	9 days
77°F (25°C)	7 days
95°F (35°C)	5 days
104°F (40°C)	4 days

Cure schedule refers to the minimum time at the specified substrate temperature prior to immersion in all chemicals as per the chemical resistance list. This does not take into consideration any specific curing requirements for third party approvals, such as for potable water use.

For storage of cargoes above ambient temperatures, consult International Protective Coatings for further details.

In common with all epoxies Interline 975P will chalk and discolour on exterior exposure. However, these phenomenon are not detrimental to chemical resistance performance.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

### SYSTEMS COMPATIBILITY

Interline 975P should be applied to properly prepared bare steel. However, where the end service use is not for potable water, the following primers are suitable;

Interline 982 for steel substrates  
Ceilcote 680M for concrete substrates

## Epoxy

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interline 975P Application Guidelines

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations. All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Base and Curing Agent if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

**Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitization if not used correctly.**

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	4.5 US gal	3 US gal	5 US gal	1.5 US gal	2 US gal
	150 US gal	100 US gal	55 US gal	50 US gal	55 US gal
For availability of other pack sizes, contact AkzoNobel.					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
	4.5 US gal	39.5 lb		14.9 lb	
	150 US gal	1266 lb		464.5 lb	
<b>Part A is supplied in two units of 633.2 lb each</b>					
STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

### Disclaimer

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 1/17/2023.