

## Alkyd

### PRODUCT DESCRIPTION

A quick drying, high gloss alkyd enamel available in a wide range of colours.

### INTENDED USES

Used as a high gloss enamel finish for interior and exterior applications. Suitable for mild industrial and commercial environments. Particularly suited for fabrication facility application.

### PRACTICAL INFORMATION FOR DEVLAC 1433

<b>Colour</b>	Wide range via the Chromascan system			
<b>Gloss Level</b>	Gloss			
<b>Volume Solids</b>	37%			
<b>Typical Thickness</b>	38-50 microns (1.5-2 mils) dry equivalent to 103-135 microns (4.1-5.4 mils) wet			
<b>Theoretical Coverage</b>	9.70 m <sup>2</sup> /litre at 38 microns d.f.t and stated volume solids 390 sq.ft/US gallon at 1.5 mils d.f.t and stated volume solids			
<b>Practical Coverage</b>	Allow appropriate loss factors			
<b>Method of Application</b>	Airless Spray, Roller, Brush			
<b>Drying Time</b>	Overcoating interval with self			
<b>Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	1.5 hours	20 hours	24 hours	Extended <sup>1</sup>
15°C (59°F)	1 hour	16 hours	24 hours	Extended <sup>1</sup>
25°C (77°F)	30 minutes	5 hours	20 hours	Extended <sup>1</sup>
40°C (104°F)	15 minutes	2 hours	6 hours	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

### REGULATORY DATA

<b>Flash Point (Typical)</b>	26°C (79°F)
<b>Product Weight</b>	1.2 kg/l (10.0 lb/gal)
<b>VOC</b>	4.49 lb/gal (539 g/l) EPA Method 24

See Product Characteristics section for further details

## Alkyd

### SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Devlac 1433 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Devlac 1433 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Devlac 1433.

### APPLICATION

<b>Mixing</b>	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.	
<b>Mix Ratio</b>	Not applicable	
<b>Airless Spray</b>	Recommended	Tip Range 0.33-0.48 mm (13-19 thou) Total output fluid pressure at spray tip not less than 141 kg/cm <sup>2</sup> (2005 p.s.i.)
<b>Air Spray (Pressure Pot)</b>	Not suitable	
<b>Brush</b>	Recommended	Typically 25-40 microns (1.0-1.6 mils) can be achieved
<b>Roller</b>	Recommended	Typically 25-40 microns (1.0-1.6 mils) can be achieved
<b>Thinner</b>	T-5 Thinner	Do not thin more than allowed by local environmental legislation
<b>Cleaner</b>	T-5 Thinner	
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with T-5 Thinner. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage.	
<b>Clean Up</b>	Clean all equipment immediately after use with T-5 Thinner. It is good working practice to periodically clean equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.  All surplus material and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

## Alkyd

### PRODUCT CHARACTERISTICS

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible.

As with all alkyd systems, Devlac 1433 has limited chemical and solvent resistance and is not suitable for use in immersion situations or in conditions of continuous condensation.

Devlac 1433 is not designed for application over epoxies or polyurethanes, and should not be applied over zinc based primers because of dangers of saponification of the alkyd resin and consequent adhesion loss.

For brush and roller application, and in some colours, two coats of Devlac 1433 may be required to give uniform coverage.

If applying Devlac 1433 in enclosed maintenance conditions ensure adequate ventilation.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

### SYSTEMS COMPATIBILITY

---

Devlac 1433 is only suitable for application over alkyd or oleoresinous priming systems, e.g.:

Devprime 1401  
Devprime 1403  
Devprime 1405  
Devprime 1407

For other suitable primers, consult International Protective Coatings.

Devlac 1433 is only suitable for overcoating with itself, and should not be topcoated with any other product.

## Alkyd

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
		1 US gal	1 US gal
	5 US gal	5 US gal	5 US gal
For availability of other pack sizes, contact International Protective Coatings.			
SHIPPING WEIGHT (TYPICAL)	Unit Size		
	1 US gal	10.6 lb	
	5 US gal	53.8 lb	
STORAGE	Shelf Life	24 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

**[www.international-pc.com](http://www.international-pc.com)**