

Enviroline® B-Flex 9400TR



Epoxy Novolac Polysulphide

PRODUCT DESCRIPTION

A solvent free, two component polysulphide lining system utilizing advanced epoxy novolac technology.

INTENDED USES

Enviroline B-Flex 9400TR uses epoxy novolac technology combined with polysulphide to give improved performance in a trowel applied system:

- Crack bridging capability (elongation to break of up to 40%)
- High cohesive strength
- Wide range of chemical resistance
- Resistance to thermal shock, wear and impact
- Ultra-low VOC
- High build single coat application
- Return to service in 4 days @ 77°F (25°C)

Applications include lining for concrete or steel surfaces that experience movement due to physical or mechanical forces, for example as a lining in bolted or riveted steel tanks. Enviroline B-Flex 9400TR is also suitable for use in secondary containment, basins and sumps, sewer manholes and pipes, wet wells, digesters and clarifiers.

PRACTICAL INFORMATION FOR ENVIROLINE B-FLEX 9400TR

Color	Tan
Gloss Level	Not applicable
Volume Solids	97%
Typical Thickness	125-250 mils (3125-6250 microns) dry equivalent to 128.9-257.7 mils (3222-6443 microns) wet
Theoretical Coverage	6 sq.ft/US gallon at 250 mils d.f.t and stated volume solids 0.20 m ² /liter at 6250 microns d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Trowel

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
77°F (25°C)	3 hours	5 hours ¹	7 hours	3 days

¹ Sufficient coating film strength has developed to permit the handling and movement of coated steelwork. A Shore D hardness reading of 50 is a recommended guideline to indicate suitability for return to service.

REGULATORY DATA

Flash Point (Typical)	Part A 151°F (66°C); Part B 151°F (66°C); Mixed 151°F (66°C)		
Product Weight	12.9 lb/gal (1.54 kg/l)		
VOC	0.26 lb/gal (32 g/lit)	EPA Method 24	
	20 g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)	

See Product Characteristics section for further details

Protective Coatings

Enviroline® B-Flex 9400TR



Epoxy Novolac Polysulphide

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Steel Substrates

Abrasive blast clean to SSPC SP10 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Enviroline B-Flex 9400TR, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

A sharp, angular profile of 3-5 mils (75-125 microns) is recommended.

Concrete Substrates

Refer to International Protective Coatings for specific recommendations.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Complete units should be stored, mixed and applied in accordance with the Enviroline Application Guidelines.	
Mix Ratio	1 part(s) : 1 part(s) by volume	
Working Pot Life	77°F (25°C) 40 minutes	104°F (40°C) 10 minutes
Plural component airless spray	Not suitable	
Airless Spray	Not suitable	
Air Spray (Pressure Pot)	Not suitable	
Brush	Not suitable	
Roller	Not suitable	
Trowel	Recommended	Refer to Enviroline Application Guidelines for more details.
Thinner	DO NOT THIN	
Cleaner	Enviroline 71C	
Work Stoppages	Thoroughly clean all equipment with Enviroline 71C. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.	
Clean Up	Clean all equipment immediately after use with Enviroline 71C. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Enviroline® B-Flex 9400TR



Epoxy Novolac Polysulphide

PRODUCT CHARACTERISTICS

The detailed Enviroline Application Guidelines should be consulted prior to use.

This datasheet provides general guidance on the use of Enviroline B-Flex 9400TR. Specific project requirements will be dependent upon the service end use and operating conditions of the tank or vessel. Always consult International Protective Coatings to confirm that Enviroline B-Flex 9400TR is suitable for contact with the product to be stored.

The detailed project coating specification provided by International Protective Coatings must be followed at all times.

Stripe coating is an essential part of good working practice and as such should form part of any lining specification.

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

Use the following chart for preferred temperature conditions. These conditions plus adequate ventilation must be maintained throughout the curing cycle.

	<u>Substrate Temperature</u>	<u>Air Temperature</u>
Preferred	70-120°F (21-49°C)	70-100°F (21-38°C)
Minimum	55°F (13°C)	55°F (13°C)

After the coating system has cured hard, the dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the minimum applied system thickness. The coating system should be free of all pinholes or other holidays. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service.

Maximum continuous dry temperature resistance for Enviroline B-Flex 9400TR is 200°F (93°C).

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also effect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

Enviroline B-Flex 9400TR should always be applied to correctly prepared substrates. When a primer is required as part of the coating specification, consult International Protective Coatings for specific advice.

Enviroline® B-Flex 9400TR



Epoxy Novolac Polysulphide

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Enviroline Application Guidelines

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations.

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Base and Curing Agent if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitization if not used correctly.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	4 US gal	2 US gal	5 US gal	2 US gal	2 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A	Part B		
	4 US gal	28.3 lb	27.2 lb		
STORAGE	Shelf Life	24 months minimum at 77°F (25°C) in original, unopened containers. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 2/5/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.