

Epoxy Novolac

PRODUCT DESCRIPTION A high solids, one coat, chemical resistant lining system with exceptional resistance to a wide range of chemicals and solvents.

INTENDED USES Ideal for industrial storage and process chemical tanks and pipelines, high pressure crude oil pipes, separation tanks and rail cars. Also used as a protective coating for highly corrosive environments.

Provides exceptional resistance over a wide range of temperatures and pressures.

PRACTICAL INFORMATION FOR DEVCHEM 253HS

Colour	Green			
Gloss Level	Semi-gloss			
Volume Solids	85% ± 2%			
Typical Thickness	300-400 microns (12-16 mils) dry equivalent to 353-471 microns (14.1-18.8 mils) wet			
Theoretical Coverage	2.13 m ² /litre at 400 microns d.f.t and stated volume solids 85 sq.ft/US gallon at 16 mils d.f.t and stated volume solids			
Practical Coverage	Allow appropriate loss factors			
Method of Application	Airless Spray, Air Spray, Brush			
Drying Time	Overcoating interval with self			
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	7 hours	46 hours	24 hours	6 days
25°C (77°F)	90 minutes	7 hours	7 hours	2.5 days
40°C (104°F)	60 minutes	2.5 hours	2.5 hours	2 days

REGULATORY DATA	Flash Point (Typical)	Part A 38°C (100°F); Part B 93°C (199°F); Mixed 38°C (100°F)		
	Product Weight	1.67 kg/l (13.9 lb/gal)		
	VOC	0.97 lb/gal (117 g/lit)	EPA Method 24	

See Product Characteristics section for further details

Epoxy Novolac

SURFACE PREPARATION

Surfaces must be dry, clean, free of oil, grease, form release agents, curing compounds, laitance, other foreign matter and be structurally sound. Remove all loose paint, mortar spatter, mill scale, and rust.

New Surfaces

Steel:

Abrasive blast to minimum SSPC-SP10 or ISO8501-1:2007 Sa2½. The blast profile should be jagged rather than “peened” and between 2 to 3 mils (50-75 microns). After blasting, vacuum or blow off all abrasive dust and ensure surface remains clean before painting.

Concrete Floors, Poured Concrete:

Cure at least 30 days. Acid etch or abrasive blast slick, glazed concrete or concrete with laitance. Prime with Pre-Prime 167 or Devchem 253HS

Previously Painted Surfaces:

Devchem 253HS may not be applied to existing coatings. All coatings must be removed and substrates treated as for New Surfaces.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.	
	Allow the mixed material to stand 15 minutes at 16-27°C (60-80°F) before use. This is not applicable for plural component application.	
Mix Ratio	4 part(s) : 1 part(s) by volume	
Working Pot Life	10°C (50°F) 7.5 hours	25°C (77°F) 3.5 hours
		40°C (104°F) 80 minutes
Airless Spray	Recommended	Tip Range 0.38-0.58 mm (15-23 thou) Total output fluid pressure at spray tip not less than 211 kg/cm ² (3000 p.s.i.) See Product Characteristics section for further details
Air Spray (Conventional)	Recommended	See Product Characteristics section for further details
Brush	Suitable - small areas only	
Thinner	Not normally required	See Product Characteristics section for further details
Cleaner	International GTA220	
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA220. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.	
Clean Up	Clean all equipment immediately after use with International GTA220. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.	
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Epoxy Novolac

PRODUCT CHARACTERISTICS

Advantages:

- Excellent chemical resistance under ambient cure conditions
- Does not require baking to cure
- High volume solids; low VOC
- Exceptional resistance to a wide variety of chemicals and solvents
- High gloss provides easy cleaning
- One coat system

Coating System: One coat of Devchem 253HS at 304-400 microns (12-16 mils) per coat. Use contrasting colours for each coat and stripe coat. Two stripe coats on all sharp edges, cutouts and welds. Note: The maximum dry film thickness of the Devchem 253HS system is 450 microns (18 mils). Dry film thickness above 450 microns (18 mils) could reduce the service life of the coating. Cure to put tank into service: 7 days with ventilation at 25°C (77°F) for maximum chemical resistance. If forced heat cure is desired, contact International Paint Protective Coatings. Apply in good climatic conditions. The temperature of the surface to be coated should be above 10°C (50°F) and at least 3°C (5°F) above the dew point.

Contact International Protective Coatings for specific cargo resistance properties.

In common with all epoxies Devchem 253HS will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Not recommended for immersion in inorganic acids.

Must not be applied over any shop or pre-construction primers.

For airless spray application: Ideally, fluid hoses should not be less than 3/8" ID and not longer than 100 feet to obtain optimum results. Longer hose length may require an increase in pump capacity, pressure, and/or thinning.

For air spray application: Use agitated spray pots, 1/2 inch ID air hoses and 1/2 inch fluid hose. Use a fluid tip of 1.78mm (0.070") or larger, a professional grade conventional gun and an air cap with good break-up. The fluid pressure should be kept low, with just enough air pressure to get good break-up of the coating.

Ventilation: It is very important for the safety of the applicator and the proper performance of the Devchem 253HS that good ventilation be provided to all portions of the enclosed area. Recommended tank ventilation involves two important phases. Phase one is to pump fresh, dehumidified air into all areas of the tank, especially "dead air" areas. Phase two is to exhaust, via an explosion proof exhaust fan, the solvent vapors from the lowest portion of the tank. This practice of pumping fresh air into the tank and exhausting solvent vapors out of the lowest part of the tank should be provided throughout the application and curing processes. This practice is to insure that all solvents are removed from the coating. Tanks must be cured 7 days at 25°C (77°F) with ventilation before being put into service. At lower temperatures, longer cure times are required.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

Devchem 253HS is designed to be topcoated with itself.

Epoxy Novolac

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	5 US gal	4 US gal	6 US gal	1 US gal	1 US gal
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
		56.1 lb		14 lb	
	5 US gal	56.1 lb		14 lb	
STORAGE	Shelf Life	24 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 03/08/2017.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com