

Water Borne Intumescent Coating

PRODUCT DESCRIPTION

A single component, borate, chlorine and APEO free, water borne intumescent coating designed for on-site application to interior exposed structural steel requiring protection from cellulosic fire.

Independently tested at accredited laboratories to BS476 Parts 20-21 and the European Standard EN 13381-8. Third party assessed and certified.

Interchar 1260 is a CE-marked product with European Technical Assessment ETA-14/0262

INTENDED USES

To provide up to 60 minutes cellulosic fire protection over a wide range of I section beams and columns and hollow sections in interior environments. Will also provide up to 90 minutes fire protection to BS476, Parts 20-21.

PRACTICAL INFORMATION FOR INTERCHAR 1260

Colour	White			
Gloss Level	Matt			
Volume Solids	73% ± 2% (measured according to ISO 3233 and BCF Guidance Method)			
Typical Thickness	200-700 microns (8-28 mils) dry equivalent to 274-959 microns (11-38.4 mils) wet			
Theoretical Coverage	1.83 m ² /litre at 400 microns d.f.t and stated volume solids 73 sq.ft/US gallon at 16 mils d.f.t and stated volume solids			
Practical Coverage	Allow appropriate loss factors			
Method of Application	Airless Spray, Brush			
Drying Time	Overcoating interval with self			
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	3 hours	4 hours	18 hours	Extended ¹
25°C (77°F)	2 hours	3 hours	6 hours	Extended ¹
40°C (104°F)	1 hour	2.5 hours	4 hours	Extended ¹

¹ See International Protective Coatings Definitions and Abbreviations

All drying time data has been quoted at the typical thickness of 500 microns (20 mils) d.f.t. Minimum overcoating intervals with approved topcoats is a minimum 24 hours.

REGULATORY DATA

Flash Point (Typical)	>100°C (>212°F)		
Product Weight	1.46 kg/l (12.2 lb/gal)		
VOC	0 g/kg	EU Solvent Emissions Directive (Council Directive 2010/75/EU)	
	23 g/lit	EU Product Directive (Council Directive 2004/42/CE)	

See Product Characteristics section for further details

Protective Coatings

Water Borne Intumescent Coating

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all steel surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 Solvent Cleaning.

Primed Steelwork

Interchar 1260 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Interchar 1260 must be applied within the overcoating intervals specified (consult the Interchar 1260 Application Guidelines).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and a full coat of primer applied prior to overcoating with Interchar 1260.

Metallic Zinc Primed Surfaces

Interchar 1260 can be applied over approved epoxy metallic zinc primers, provided that these have been overcoated with an approved tie coat. Ensure that the primed surface is clean, dry and free from contamination prior to application of the Interchar 1260. Recommended tie coats are Intergard 269 or Intergard 276.

APPLICATION

Mixing	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.	
Mix Ratio	Not applicable	
Airless Spray	Recommended	Tip Range 0.39-0.54 mm (15-21 thou) Total output fluid pressure at spray tip not less than 175 kg/cm ² (2489 p.s.i.)
Air Spray (Pressure Pot)	Not recommended	
Air Spray (Conventional)	Not suitable	
Brush	Small areas only	Typically 2.0-7.0 mils (50-175 microns) can be achieved
Thinner	Not recommended	
Cleaner	Clean Water	
Work Stoppages	Do not allow material to remain in hoses, guns or spray equipment. Thoroughly flush all equipment with clean water. Do not use organic solvents. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning after storage.	
Clean Up	Clean all equipment immediately after use with clean water. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Water Borne Intumescent Coating

PRODUCT CHARACTERISTICS

The detailed Interchar 1260 Application Guidelines should be consulted prior to use.

Interchar 1260 must be protected from freezing at all times during storage and transport.

For optimum application and drying characteristics, the air and substrate temperature should be greater than 10°C (50°F) and relative humidity less than 85%. Good air flow and ventilation should be maintained to improve drying and recoat properties and speed up the application. Application at temperatures below 10°C (50°F) will retard drying and extend overcoatings intervals, as will higher humidities.

Discard frozen Interchar 1260 in accordance with local disposal regulations. Do not thaw frozen material and apply.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

In line with good painting practice, application should not take place in conditions which are deteriorating, e.g. the temperature is falling or there is a risk of condensation forming.

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved.

Care must be taken not to over-apply on areas such as internal angles, corners, edges, etc.

The finished appearance of Interchar 1260 is dependent upon application method. For visible areas spray application is recommended. Higher decorative finishes may require additional preparation before application of topcoats; please see Application Guidelines for further information. Topcoats are not necessary for in environments classified as ISO 12944-2 C1 and may be specified purely for decorative reasons.

Interchar 1260 (whether sealed or not) should be protected from pooling or running water.

Interchar 1260 is intended for application to internal steelwork in unexposed conditions. Consult International Paint for the appropriate primer and topcoat systems for the specified interior environment.

Interchar 1260 is not designed for frequent water immersion/soaking.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

The following primers are recommended for Interchar 1260:

Intercryl 525	Intergard 251
Intergard 269	Intergard 276
Interprime 306	Interseal 1052

Interchar 1260 may also be applied over Interzinc 42 and 52 providing a suitable tie coat is also used; please see Surface Preparation section.

The following topcoats are recommended for Interchar 1260:

Intercryl 525	Interthane 870
Intersheen 579	Interthane 990
Interthane 990SG	

There is a wider range of primers and topcoats which may be suitable for use with Interchar 1260; please contact International Protective Coatings for further information and assistance.

Water Borne Intumescent Coating

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
	20 litre	20 litre	20 litre
For availability of other pack sizes, contact International Protective Coatings.			

SHIPPING WEIGHT (TYPICAL)	Unit Size	
	20 litre	30.5 kg

STORAGE	Shelf Life	
		12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 09/03/2020.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com