

Silicone Elastomer

PRODUCT DESCRIPTION A three component, silicone elastomer finish coat, with no added biocides.

INTENDED USES As the finish coat for the Intersleek fouling control system.

To provide a biocide-free alternative to conventional anti-fouling. Low surface energy provides the product with easy clean characteristics to minimise cleaning costs associated with fouling removal.

Suitable for use on structures in areas where conventional toxic antifouling are not permitted due to environmental concerns, including offshore structures and power station water inlets.

PRACTICAL INFORMATION FOR INTERSLEEK 425

Color Black, Grey, White, Yellow

Gloss Level Gloss

Volume Solids 72%

Typical Thickness 6 mils (150 microns) dry equivalent to 8.3 mils (208 microns) wet

Theoretical Coverage 192 sq.ft/US gallon at 6 mils d.f.t and stated volume solids
4.80 m²/liter at 150 microns d.f.t and stated volume solids

Practical Coverage Allow appropriate loss factors

Method of Application Airless Spray, Air Spray, Brush

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
50°F (10°C)	8 hours	10 hours	12 hours	Extended ¹
59°F (15°C)	6 hours	8 hours	10 hours	Extended ¹
77°F (25°C)	3 hours	5 hours	6 hours	Extended ¹
104°F (40°C)	45 minutes	60 minutes	2 hours	Extended ¹

¹ See International Protective Coatings Definitions & Abbreviations

REGULATORY DATA **Flash Point (Typical)** Part A 95°F (35°C); Part B 77°F (25°C); Part C 77°F (25°C); Mixed 77°F (25°C)

Product Weight 9.2 lb/gal (1.1 kg/l)

VOC 2.11 lb/gal (254 g/lit) EPA Method 24
241 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC)

See Product Characteristics section for further details

Silicone Elastomer

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Steel Substrates

Intersleek 425 should always be applied over a recommended anti-corrosive coating scheme which has been overcoated with Intersleek 167 adhesion modifier and Intersleek 386 tie coat (Intersleek 381 tie coat in North America). The primer surface should be dry and free from all contamination, and Intersleek 425 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP10, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed with the full priming system prior to the application of Intersleek 425.

Flexible Substrates

Intersleek 425 should be applied over a correctly prepared substrate which has been primed using Intersleek 386 (Intersleek 381 in North America). Consult the relevant product data sheet for details.

Consult your local representative for these substrates.

APPLICATION

Mixing	Material is supplied in three containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	<ol style="list-style-type: none"> (1) Agitate Base (Part A) with a power agitator. (2) Agitate Curing Agent (Part B) with a power agitator. (3) Combine entire contents of Base (Part A), Curing Agent (Part B) and Accelerator and mix thoroughly with power agitator. 			
Mix Ratio	7.5 part(s) : 2.0 part(s) : 0.5 part(s) by volume			
Working Pot Life	50°F (10°C) 2 hours	59°F (15°C) 90 minutes	77°F (25°C) 60 minutes	104°F (40°C) 20 minutes
Airless Spray	Recommended	Tip Range 17-21 thou (0.43-0.53 mm) Total output fluid pressure at spray tip not less than 3000 psi (211 kg/cm ²)		
Air Spray (Conventional)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
Brush	Suitable - Small areas only	Typically 3.0-4.0 mils (75-100 microns) can be achieved		
Roller	Not suitable			
Thinner	International GTA007	Do not thin more than allowed by local environmental legislation		
Cleaner	International GTA007, International GTA822 (or International GTA415)			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA007, International GTA822 (or International GTA415) . Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA007, International GTA822 (or International GTA415). It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Silicone Elastomer

PRODUCT CHARACTERISTICS

This product contains silicones which can cause problems with the surface finish and subsequent adhesion of other coatings if contaminated with Intersleek 425. Good housekeeping practices are essential and care should be taken to avoid overspray onto conventionally coated areas. **All** equipment must be thoroughly cleaned prior to use, and before re-use with other materials, to prevent contamination.

Any liquids used to clean up Intersleek must not be allowed to contaminate other liquid paints or coated surfaces.

Intersleek 425 has a short pot life. Mix full units only and use within the pot life specified.

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved. Application by air spray may require a multiple cross spray pattern to attain maximum film build. Lower or high temperatures may require specific application techniques to achieve maximum film build.

When applying Intersleek 425 by brush, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

This product will not cure adequately below 41°F (5°C). For maximum performance ambient curing temperatures should be above 50°F (10°C).

Exposure to unacceptably low temperatures and/or high humidities during, or immediately after, application may result in incomplete cure and surface contamination that could jeopardize subsequent intercoat adhesion. Minimum application temperature is 50°F (10°C) and minimum relative humidity is 30%.

Over-application of Intersleek 425 will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

In common with all silicone elastomers the surface finish produced provides a relatively soft, rubbery finish which is resistant to direct impact but can be damaged by mechanical means such as gouging, scratching and scraping. When handling steelwork coated with Intersleek 425 it is recommended that chains are not used and lifting is conducted by means of nylon slings.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also effect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

Intersleek 425 must be applied over an approved epoxy anti-corrosive scheme which has been overcoated with Intersleek 167 Adhesion Modifier and Intersleek 386 Tie Coat (Intersleek 381 in North America).

In certain circumstances where approved anti-corrosive systems are specified, and short overcoating times can be achieved, it may be possible to apply Intersleek 425 over Intersleek 386 tie coat (Intersleek 381 in North America), without the need for Intersleek 167 adhesion modifier. Consult International Protective Coatings for specific recommendations.

This product should only be topcoated with itself, and should never be overcoated with another product.

Silicone Elastomer

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B		Part C	
		Vol	Pack	Vol	Pack	Vol	Pack
	1 US gal	0.75 US gal	1 US gal	0.2 US gal	0.25 US gal	0.05 US gal	0.06 US gal
	5 liter	3.75 liter	5 liter	1 liter	1 liter	0.25 liter	0.38 liter

For availability of other pack sizes contact International Protective Coatings

SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A	Part B	Part C
	1 US gal	7.3 lb	2 lb	0.4 lb
	5 liter	4.7 kg	1.1 kg	0.3 kg

STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	--

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Issue date: 9/15/2015

Copyright © AkzoNobel, 9/15/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com