

# Intercure 4500

## Maximize productivity

Our high performance Intercure<sup>®</sup> 4500 semi-gloss primer finish can vastly improve your productivity. Excellent anti-corrosion and aesthetic properties allow you to replace traditional multi-coat systems with a single coat either direct to metal or over a primer.

Productivity is further enhanced with hard dry times as low as two hours at 77°F (25°C) 50% relative humidity

- Semi-gloss polyaspartic primer finish
- Outstanding corrosion performance in a single coat either direct to metal or over a primer
- Rapid cure even at low temperatures
- Improved UV durability versus traditional polyurethane topcoats
- High solids, low VOC



# "This coating is what our process needs"

North American Tank Fabricator

When it comes to protective coatings, time is precious. Intercure<sup>®</sup> 4500 reduces the number of coats required and dries quickly even at low temperatures, maximizing productivity in more ways than one.

## Reduces the number of coats

The high build characteristics and outstanding anti-corrosive and UV performance of polyaspartic resin technology means that Intercure<sup>®</sup> 4500 can do the job of two products, replacing a high build primer or intermediate and aesthetic topcoat in one coat.

## Rapid cure even at low temperatures

A unique feature of Intercure<sup>®</sup> 4500 is its rapid cure ability even at low temperatures. This maximizes productivity, allows use in colder climates and reduces the need for forced drying equipment, meaning facilities can cut heating costs and reduce environmental impact.

## Benefits throughout the contract chain


Whether an applicator, contractor or owner, in today's competitive market it is essential that you make the most of your assets, delivering on time and without compromise. Intercure<sup>®</sup> 4500 has been engineered to boost productivity while offering outstanding performance; maximizing output from paint shops, allowing contractors to meet deadlines and giving owners a functional facility ahead of schedule.

## Lower VOC emissions

The high solids and low VOC of Intercure<sup>®</sup> 4500, combined with a reduction in the number of coats required can help to reduce overall VOC emissions.

Please consult your local representative for a list of approved primers.

## Faster handling



## Technical information

<b>Color</b>	Limited color range available		
<b>Volume solids</b>	77% ±1%		
<b>Film thickness</b>	6-10 mils (150-250 microns)		
<b>Mix ratio</b>	4:1 by volume		
<b>Temperature</b>	Touch dry*	Hard dry*	Min. recoat*
41°F (5°C)	60 minutes	3½ hours	3½ hours
59°F (15°C)	45 minutes	2½ hours	2½ hours
77°F (25°C)	30 minutes	2 hours	2 hours
104°F (40°C)	15 minutes	1½ hours	1½ hours
<b>VOC's</b>	1.87 lb/gal (225 g/lit) - EPA Method 24 (153g/kg) - EU Solvent Emissions Directive (Council Directive 1999/13/EC)		

\*The dry times quoted have been determined at the temperature indicated and 50% relative humidity

## Test data

	TEST METHOD	SPECIFICATION DETAILS	RESULTS
<b>Corrosion resistance</b>	ISO 12944 - "Corrosion protection of steel structures by protective paint systems"	1 x 7 mils (175 µm) DFT applied directly to Sa2½ blasted steel	Meets the performance criteria for a C3 corrosive environment as set out in Part 6 of the standard
		1 x 7 mils (175 µm) DFT applied over 3 mils (75 µm) of zinc rich primer	Meets the performance criteria for a C5 environment as set out in part 6 of the standard
<b>Gloss retention</b>	ASTM G154 - "Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of non-metallic materials"	1 x 6-8 mils (150-200 µm) DFT applied directly to aluminum Q Panels	Typical gloss retention not less than 60% following 3000 hours exposure to UVA340 type fluorescent lamps
<b>Abrasion</b>	ASTM D4060 - "Abrasion Resistance of Coatings via the Taber Abraser"	1 x 6-8 mils (150-200 µm) DFT applied directly to Sa2½ blasted steel	Average 80 mg weight loss per 1000 cycles using CS10 wheels and a 1kg loading
<b>Flexibility</b>	ASTM D522 - "Mandrel Bend Test of Attached Organic Coatings" - Conical Mandrel Test	1 x 6-8 mils (150-200 µm) DFT applied directly to Sa2½ blasted steel	An average of 7.5% elongation of the coating is achieved prior to fracture
<b>Impact</b>	ASTM D2794 - "Resistance to the Effects of Rapid Deformation (Impact)"	1 x 6-8 mils (150-200 µm) DFT applied directly to Sa2½ blasted steel	Direct Impact Resistance - 10 Joules

[www.international-pc.com](http://www.international-pc.com)  
[pcmarketing.americas@akzonobel.com](mailto:pcmarketing.americas@akzonobel.com)

All trademarks mentioned in this publication are owned by the AkzoNobel group of companies. © Akzo Nobel 2014.

AkzoNobel has used its best endeavors to ensure that the information contained in this publication is correct at the time of printing. Please contact your local representative if you have any questions.

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale.