

## Universal Pipe Coating

### PRODUCT DESCRIPTION

A high temperature universal pipe coating (UPC) that complies with the performance criteria of ISO12944-9 standard for corrosion protection in offshore environments.

Interbond 1202UPC is a two component, ambient cure, inorganic copolymer.

Conforms to the inert multi-polymeric matrix coating definition as per NACE SP0198 standard.

### INTENDED USES

Suitable for protecting above-ground piping and accessories operating at temperatures between -321°F (-196°C) to 1202°F (+650°C).

Interbond 1202UPC reduces paint complexity and overall painting costs of new construction projects by simplifying coating specifications for process piping and accessories.

Designed as a two coat or single coat application to carbon or stainless steel for long term corrosion protection.

Suitable for use on surfaces either uninsulated or under thermal insulation and for the protection of cryogenic piping and equipment. Not suitable for buried service.

### PRACTICAL INFORMATION FOR INTERBOND 1202UPC

<b>Color</b>	Metallic Gray
<b>Gloss Level</b>	Matte
<b>Volume Solids</b>	56%
<b>Typical Thickness</b>	4-8 mils (100-200 microns) dry equivalent to 7.2-14.3 mils (179-357 microns) wet
<b>Theoretical Coverage</b>	225 sq.ft/US gallon at 4 mils d.f.t and stated volume solids 5.60 m <sup>2</sup> /liter at 100 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Air Spray, Brush, Conventional Spray, Roller
<b>Drying Time</b>	

Overcoating interval with self

Temperature	Touch Dry	Hard Dry	Minimum	Maximum
50°F (10°C)	90 minutes	6 hours	6 hours	14 days
59°F (15°C)	60 minutes	6 hours	6 hours	14 days
77°F (25°C)	30 minutes	3 hours	6 hours	14 days
104°F (40°C)	15 minutes	3 hours	6 hours	14 days

Where maximum overcoating intervals are exceeded, clean the surface of Interbond 1202UPC thoroughly with clean fresh water then lightly abrade.

### REGULATORY DATA

**Flash Point (Typical)** Part A 99°F (37°C); Part B 169°F (76°C); Mixed 102°F (39°C)

**Product Weight** 10.4 lb/gal (1.25 kg/l)

**VOC** 3.42 lb/gal (410 g/lit) EPA Method 24  
311 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC)  
405 g/lit Chinese National Standard GB23985

See Product Characteristics section for further details

## Protective Coatings

## Universal Pipe Coating

### SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

#### Abrasive Blast Cleaning

Abrasive blast clean to SSPC SP10 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Interbond 1202UPC, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

#### Power Tool Cleaning (Small Areas Only)

For small areas of touch up and repair, Power Tool cleaning to SSPC SP11 is suitable. Optimum performance will be achieved with a minimum surface profile of 2 mils (50 microns).

#### Austenitic Stainless Steel

Ensure surface is clean, dry and free from metal corrosion products prior to application. Abrasive blast with nonmetallic and chloride free abrasive (e.g. aluminium oxide or garnet) to obtain anchor profile of 1.5 to 2 mils (37.5 to 50 microns).

Optimum performance will be achieved for steel operating under high & cyclic temperature conditions when the preferred 2 mil (50 micron) profile is obtained.

#### Primed Surfaces

Interbond 1202UPC is suitable for application to unweathered steelwork freshly coated with zinc silicate shop primers. If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be blast cleaned to SSPC-SP6 or Sa2½ (ISO 8501-1:2007).

### APPLICATION

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed, it must be used within the working pot life specified.			
	(1)	Agitate Base (Part A) with a power agitator.		
	(2)	Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
	Refer to Interbond 1202UPC Application Guidelines for more details.			
<b>Mix Ratio</b>	28 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	50°F (10°C)	59°F (15°C)	77°F (25°C)	104°F (40°C)
	8 hours	8 hours	8 hours	4 hours
<b>Airless Spray</b>	Recommended	Tip Range 23-27 thou (0.58-0.69 mm) Total output fluid pressure at spray tip not less than 2005 psi (141 kg/cm²) To ensure easy application, all filters should be removed from the pump and gun.		
<b>Air Spray (Pressure Pot)</b>	Recommended when topcoating	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
<b>Air Spray (Conventional)</b>	Recommended when topcoating	Use suitable proprietary equipment.		
<b>Brush</b>	Suitable - touch up only	Typically 2.4 mils (60 microns) can be achieved		
<b>Roller</b>	Suitable - touch up only	Typically 2.4 mils (60 microns) can be achieved		
<b>Thinner</b>	International GTA007	Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.		
<b>Cleaner</b>	International GTA007	Choice of cleaner may be subject to local legislation. Please consult your local representative for specific advice.		
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA007. Once units of material have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

## Universal Pipe Coating

### PRODUCT

The detailed Interbond 1202UPC Application Guidelines should be consulted prior to use.

### CHARACTERISTICS

Interbond 1202UPC conforms to the Inert Multipolymeric Matrix coating definition as per NACE Standard Practice SP0198 Table 2 typical recommendations for use on carbon steel equipment under thermal insulation.

When applying Interbond 1202UPC in confined spaces, ensure adequate ventilation.

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

Interbond 1202UPC reacts with atmospheric moisture, and as such when in the can should remain covered at all times. Failure to keep tin covered will result in skinning of unused material and loss of pot life.

In common with many products containing leafing aluminum pigmentation Interbond 1202UPC may be prone to developing a "polished" appearance in areas of minor mechanical impact etc. However, this phenomenon is merely aesthetic and is not detrimental to the anti-corrosive performance of the product.

As with all coated surfaces, it is recommended that appropriate care be taken during storage and transport to avoid mechanical damage from dragging and scraping.

Due to the flexible nature of the coating and total recommended dry film thickness being at a minimum of 8 mils (200 microns), pull-off adhesion testing (as per ISO 4624) is not considered relevant. Adhesion should be evaluated using cross cut methods as specified in ASTM D3359. Acceptable rating achieved in practice is  $\geq 3A$ .

When using in high heat service over inorganic zinc primer, the products should be applied in strict accordance with film thickness specifications, since application of excessive thicknesses may cause blistering or adhesion loss. Determine that the inorganic zinc primer is thoroughly cured prior to application of the high heat coating by following the curing instructions given on the relevant product data sheet.

When using a zinc silicate primer, the recommended thickness of zinc silicate is 2 mils (50 microns) dry film thickness to ensure maximum surface strength for any subsequent temperature cycling and to avoid flaking of topcoats. The maximum subsequent single coat thickness of Interbond 1202UPC should be 6 mils (150 microns), with a maximum total system dry film thickness of 12 mils (300 microns). It is preferable to overcoat zinc silicate before weathering but in cases where this is not possible then the zinc silicate surface should be clean and free of zinc corrosion products.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

### SYSTEMS COMPATIBILITY

Interbond 1202UPC is normally applied direct to metal. This specialist coating is only compatible with a very limited number of products.

Suitable primers are:

Interzinc 22 Series

Overcoating of Interbond 1202UPC for color identification purposes may be possible.

Suitable topcoats are:

Interthane 990  
Intertherm 875

For other suitable topcoats, consult International Protective Coatings.

## Universal Pipe Coating

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interbond 1202UPC Application Guidelines

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	15 liter	14.48 liter	20 liter	0.52 liter	0.75 liter
	5 US gal	3.82 US gal	5 US gal	0.18 US gal	0.25 US gal
	1 US gal	0.77 US gal	1 US gal	0.03 US gal	1 US pint

For availability of other pack sizes contact International Protective Coatings

SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A	Part B
	15 liter	19.6 kg	0.61 kg
	5 US gal	43.9 lb	1.7 lb
	1 US gal	8.7 lb	0.4 lb

STORAGE	Shelf Life
	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

### Disclaimer

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 9/7/2021.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

**[www.international-pc.com](http://www.international-pc.com)**