

PRODUCT DESCRIPTION

A two component, acrylic aliphatic polyurethane finish giving excellent outdoor durability, gloss retention and long term recoatability.

INTENDED USES

Suitable for use on earth moving equipment, OEM applications, pumps, valves, machinery etc. where high gloss retention and aesthetics are required.

PRACTICAL INFORMATION FOR INTERTHANE 1022

Colour	Caterpillar Yellow			
Gloss Level	High Gloss			
Volume Solids	51% ± 2%			
Typical Thickness	50-75 microns (2-3 mils) dry equivalent to 98-147 microns (3.9-5.9 mils) wet			
Theoretical Coverage	10.20 m ² /litre at 50 microns d.f.t and stated volume solids 409 sq.ft/US gallon at 2 mils d.f.t and stated volume solids			
Practical Coverage	Allow appropriate loss factors			
Method of Application	Airless Spray, Air Spray, Brush, Roller			
Drying Time	Overcoating interval with self			
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
15°C (59°F)	3 hours	16 hours	16 hours	Extended ¹
25°C (77°F)	2.5 hours	8 hours	8 hours	Extended ¹
40°C (104°F)	1.5 hours	3 hours	3 hours	Extended ¹

¹ See International Protective Coatings Definitions and Abbreviations. If overcoating after more than 48 hours, the surface should first be lightly abraded with fine emery paper

REGULATORY DATA

Flash Point	Part A 25°C (77°F); Part B 34°C (93°F); Mixed 28°C (82°F)	
Product Weight	1.17 kg/l (9.8 lb/gal)	
VOC	485 g/l (4.04 lb/gal)	(Calculated)

See Product Characteristics section for further details

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Primed Surfaces

Interthane 1022 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Interthane 1022 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC SP6 Abrasive Blasting or SSPC SP11, Power Tool Cleaning) and patch primed prior to the application of the product.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.		
	(1) Agitate Base (Part A) with a power agitator.		
	(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
Mix Ratio	6 part(s) : 1 part(s) by volume		
Working Pot Life	5°C (41°F) 12 hours	15°C (59°F) 6 hours	25°C (77°F) 40°C (104°F) 2 hours 2 hours
Airless Spray	Recommended	Tip Range 0.33-0.45 mm (13-18 thou) Total output fluid pressure at spray tip not less than 155 kg/cm ² (2204 p.s.i.)	
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E
Air Spray (Conventional)	Suitable	Use suitable proprietary equipment	
Brush	Suitable	Typically 50-75 microns (2.0-3.0 mils) can be achieved	
Roller	Suitable	Typically 50-75 microns (2.0-3.0 mils) can be achieved	
Thinner	International GTA102	Do not thin more than allowed by local environmental legislation	
Cleaner	International GTA102		
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA102. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.		
Clean Up	Clean all equipment immediately after use with International GTA102. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.		
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		

**PRODUCT
CHARACTERISTICS**

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible. Best results in terms of gloss and appearance will always be obtained by conventional air spray application.

For brush application, multiple coats of Interthane 1022 may be required to give uniform coverage when applying over dark undercoats. Best practice is to use a colour compatible intermediate or anticorrosive coating under the Interthane 1022.

When overcoating after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as oil, grease, salt crystals and traffic fumes, before application of a further coat of Interthane 1022.

Absolute measured adhesion of topcoats to aged Interthane 1022 is less than that to fresh material, however, it is adequate for the specified end use.

This product must only be thinned using the recommended International thinners. The use of alternative thinners, particularly those containing alcohols, can severely inhibit the curing mechanism of the coating.

Do not apply at steel temperatures below 5°C (41°F).

When applying Interthane 1022 in confined spaces ensure adequate ventilation.

Condensation occurring during or immediately after application may result in a matt finish and an inferior film.

This product is not recommended for use in immersion conditions. When severe chemical or solvent splashing is likely to occur contact International Protective Coatings for information regarding suitability.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**SYSTEMS
COMPATIBILITY**

The following primers are recommended for Interthane 1022:

Intergard 1032

Interthane 1022 is designed to be topcoated with itself.

For other suitable approved products contact International Protective Coatings.

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

Warning: Contains isocyanate. Wear air-fed hood for spray application.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	5 litre	4.28 litre	5 litre	0.72 litre	1 litre
	20 litre	17.14 litre	20 litre	2.86 litre	3 litre
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	5 litre	5.18 kg		0.71 kg	
	20 litre	20.74 kg		2.85 kg	
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

Copyright © AkzoNobel, 14/08/2009.

 International, International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

www.international-pc.com