

## Alkyd

### PRODUCT DESCRIPTION

A rust inhibitive primer for use over properly prepared steel. A general purpose shop primer, Devprime 1401 offers low cost, easy application and low VOC.

### INTENDED USES

An economical general purpose shop primer for structural steel in mild industrial and commercial environments. Suitable for use on metal parts, fabricated structures, machinery and other ferrous metal surfaces.

### PRACTICAL INFORMATION FOR DEVPRIME 1401

<b>Colour</b>	Red, Grey
<b>Gloss Level</b>	Not applicable
<b>Volume Solids</b>	55%
<b>Typical Thickness</b>	25-50 microns (1-2 mils) dry equivalent to 45-91 microns (1.8-3.6 mils) wet
<b>Theoretical Coverage</b>	11 m <sup>2</sup> /litre at 50 microns d.f.t and stated volume solids 441 sq.ft/US gallon at 2 mils d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Roller, Air Spray, Brush
<b>Drying Time</b>	

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
10°C (50°F)	30 minutes	2.5 hours	2 hours	Extended <sup>1</sup>
15°C (59°F)	20 minutes	2 hours	1.5 hours	Extended <sup>1</sup>
25°C (77°F)	15 minutes	1 hour	1 hour	Extended <sup>1</sup>
40°C (104°F)	5 minutes	45 minutes	45 minutes	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

### REGULATORY DATA

<b>Flash Point (Typical)</b>	23°C (73°F)
<b>Product Weight</b>	1.47 kg/l (12.3 lb/gal)
<b>VOC</b>	3.29 lb/gal (395 g/l) EPA Method 24

See Product Characteristics section for further details

## Alkyd

### SURFACE PREPARATION

The performance of this product will depend upon the degree of surface preparation. The surface to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

#### Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Devprime 1401 is suitable for application to blast cleaned surfaces which were initially to the above standard but have been allowed to deteriorate under good shop conditions for up to 7-10 days. The surface may deteriorate to Sa2 standard but must be free from loose powdery deposits.

#### Maintenance and Site Touch-up

The product is designed for application to surfaces prepared to St2 (ISO 8501-1:2007) or SSPC-SP2. When using power tools care should be taken to avoid surface polishing. The product may also be applied to surfaces which have been brush blasted to Sa1 (ISO 8501-1:2007) or SSPC-SP7. On poor surfaces brush application will assist performance.

Devprime 1401 is suitable for overlap onto most aged coating systems. Loose or flaking coatings should be removed back to a firm edge. Glossy epoxies and polyurethanes may require abrasion.

### APPLICATION

<b>Mixing</b>	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.		
<b>Airless Spray</b>	Recommended	Tip Range 0.38-0.43 mm (15-17 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2503 p.s.i.)	
<b>Air Spray (Pressure Pot)</b>	Recommended	Gun	DeVilbiss MBC or JGA
		Air Cap	704
		Fluid Tip	E
<b>Brush</b>	Suitable	Typically 40-50 microns (1.6-2.0 mils) can be achieved	
<b>Roller</b>	Suitable	Typically 40-50 microns (1.6-2.0 mils) can be achieved	
<b>Thinner</b>	T-5 Thinner	Do not thin more than allowed by local environmental legislation	
<b>Cleaner</b>	T-5 Thinner		
<b>Work Stoppages</b>	Thoroughly flush all equipment with T-5 Thinner. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.		
<b>Clean Up</b>	Clean all equipment immediately after use with T-5 Thinner. It is good working practice to periodically clean equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.		
	All surplus material and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		

## Alkyd

### PRODUCT CHARACTERISTICS

Anti-corrosive performance on hand prepared steel is related directly to both the degree of surface preparation and the dry film thickness of the system applied.

This product is not intended for use in aggressive, corrosive environments, or on heavily pitted or contaminated steel.

When applying Devprime 1401 by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

Where a durable cosmetic finish with good gloss and colour retention is required overcoat with recommended topcoats.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

If applying Devprime 1401 in enclosed maintenance conditions ensure adequate ventilation.

Over-application of Devprime 1401 will extend both the minimum overcoating intervals and handling times, may be detrimental to long term overcoating, performance properties and may give rise to wrinkling.

#### Low Temperature Curing

<u>Temperature</u>	<u>Touch Dry</u>	<u>Hard Dry</u>	<u>Overcoating Interval with recommended topcoats</u>	
			<u>Minimum</u>	<u>Maximum</u>
5°C (41°F)	1 hour	4 hours	2 hours	Extended*

\* See International Protective Coatings Definitions and Abbreviations

Devprime 1401 meets CISC 2-75 and 1-73a Performance Specification with exception of Drying Time (para. 5.2).

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

### SYSTEMS COMPATIBILITY

---

Devprime 1401 is normally applied to blasted or hand or power tool cleaned steel.

The following topcoats are recommended for Devprime 1401:

Devlac 1431  
Devlac 1433

For other suitable topcoats, consult International Protective Coatings.

## Alkyd

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
		1 US gal	1 US gal
	5 US gal	5 US gal	5 US gal
For availability of other pack sizes, contact International Protective Coatings.			
SHIPPING WEIGHT (TYPICAL)	Unit Size		
	1 US gal	28.8 lb	
	5 US gal	65 lb	
STORAGE	Shelf Life	24 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

[www.international-pc.com](http://www.international-pc.com)