

PRODUCT DESCRIPTION

Intertherm 7050 is a high performance thermal insulation system based on a solvent free, 100% solids, epoxy syntactic foam.

Designed to provide both thermal insulation and corrosion protection in its own right and also when used as part of the Chartek fireproofing system.

Suitable for use at continuous operating temperatures from -40°F (-40°C) up to +248°F (+120°C).

Application techniques include spray, trowel and moulding/casting.

Intertherm 7050 is impervious to moisture and is extremely resilient to damage and chemical spills

INTENDED USES

Thermal Insulation: To provide thermal insulation of pipes, ductwork, vessels and equipment operating at temperatures between -40°F (-40°C) and +248°F (+120°C) for either heat conservation or personnel protection.

Fire Protection: Intertherm 7050 may also be used as an underlayment or overlayment for International Protective Coatings' Chartek fireproofing systems, allowing Chartek's use on substrates operating between 176°F (80°C) and 248°F (120°C) or to provide protection to Chartek from external heat sources.

Preventing Corrosion Under Insulation: In addition to its insulation properties, Intertherm 7050 provides excellent long term corrosion protection thereby removing corrosion under insulation (CUI) concerns associated with traditional insulation systems. Requiring no external cladding, its high compressive and impact strength provides tremendous durability, eliminating the problem of damage to insulation from foot traffic and accidental loads.

Thermal Shock Protection: Tested and proven in cryogenic spills to prevent the effects of low temperature embrittlement of steel or thermal shock cracking/spalling of concrete. When used with Chartek fireproofing systems Intertherm 7050 can be used to provide combined thermal shock and fire protection from incidents such as spills and ruptures at LNG processing and storage facilities.

Not to be used in areas where only 'non-combustible' materials are permitted.

PRACTICAL INFORMATION FOR INTERTHERM 7050

Color	Pale pink when mixed (Part A - Pink; Part B - White)
Gloss Level	Not applicable
Volume Solids	100%
Typical Thickness	Dependent on insulation and anti-corrosive requirements. Typically 0.2 - 2 inches (5 - 50 mm)
Density	Nominal: 36 lb/cu.ft. (0.57g/cm ³) Note: Final density depends on method of application and may vary. Typically, spray density will be up to 7% above nominal
Method of Application	Trowel, Hot Twin Feed Airless Spray

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
50°F (10°C)	4 hours	30 hours	4 hours	48 hours
59°F (15°C)	2 hours	12 hours	2 hours	48 hours
77°F (25°C)	1 hour	6 hours	2 hours	48 hours
104°F (40°C)	1 hour	4 hours	1 hour	24 hours

Dry times determined at 1 inch (25 mm) dry film thickness. For extended overcoating intervals please consult International Protective Coatings.

REGULATORY DATA **Flash Point (Typical)** Part A >223°F (106°C); Part B >223°F (106°C); Mixed >223°F (106°C)

VOC 0.00 lb/gal (0 g/lt)
0 g/kg EPA Method 24
EU Solvent Emissions Directive
(Council Directive 1999/13/EC)

See Product Characteristics section for further details

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Abrasive Blast Cleaning

Abrasive blast cleaning to SP10 or Sa2½ (ISO 8501-1:2007) is the preferred method of surface preparation, however commercial blast cleaning to SSPC-SP6 or Sa2 (ISO 8501-1:2007) is acceptable when a suitable primer is used. Intertherm 7050 may be applied directly to the blast cleaned substrate or over an approved anti-corrosive primer. If oxidation has occurred between blasting and application of primer or Intertherm 7050, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

A sharp, angular surface profile of 2-3 mils (50-75 microns) is recommended.

Primed Surfaces

Intertherm 7050 can be applied over approved anti-corrosive primers. The primer surface should be dry and free from all contamination, and Intertherm 7050 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. SSPC-SP10 or Sa2½ (ISO 8501-1:2007) Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning, and patch primed prior to the application of Intertherm 7050.

For surfaces abrasive blast cleaned to SSPC-SP10 or Sa2½ (ISO 8501-1:2007), the preferred primer for high temperature service is Intertherm 228 applied at a dry film thickness of 3-4 mils (75-100 microns).

For surfaces abrasive blast cleaned to SSPC-SP6 or Sa2 (ISO 8501-1:2007) or power tool cleaned to SSPC-SP11, the preferred primer for high temperature service is Interplus 256 applied to a dry film thickness of 6-8 mils (150-200 microns).

APPLICATION

Mixing	<p>Hand Application Individual components must be stored at 70-90°F (21-32°C) for 24 hours prior to mixing. Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.</p> <ol style="list-style-type: none"> (1) Agitate Base (Part A) with a power agitator. (2) Agitate Curing Agent (Part B) with a power agitator. (3) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator. <p>Plural Component Spray Application Consult Intertherm 7050 Application Manual</p>		
Mix Ratio	Always mix full units.		
Working Pot Life	50°F (10°C) 30 minutes	59°F (15°C) 30 minutes	77°F (25°C) 15 minutes
Plural component airless spray	Recommended	Consult Intertherm 7050 Application Manual	
Trowel	Recommended	<p>Application is carried out using standard plastering techniques. The first coat should be hand trowelled to ¼-½ inch (3-6 mm) thickness to ensure full wetting of the substrate. The final surface should be rolled to remove trowel marks and high spots and achieve a uniform thickness. Use short nap rollers dampened with International GTA123. When the required total film thickness cannot be reached in one shift, the Intertherm 7050 surface should be scratched to provide a key for subsequent coats.</p>	
Thinner Cleaner	DO NOT THIN International GTA822		
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.		
Clean Up	<p>Clean all equipment immediately after use with International GTA822. It is good working practice to periodically clean equipment during the course of the working day. Frequency of cleaning will depend upon amount used, temperature and elapsed time, including any delays.</p> <p>All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.</p>		

PRODUCT CHARACTERISTICS

The following conditions shall apply (or be generated) throughout the application:-

Minimum Air Temperature	50°F (10°C) - Recommended
Maximum Humidity	85%
Surface Temperature	A minimum of 5°F (3°C) above dew point of surrounding air.

General

All surfaces to be coated should be clean and dry at all times. Intertherm 7050 may be applied when the surrounding air temperature is at a minimum of 41°F (5°C) as long as the surface temperature is at least 5°F (3°C) above the dew point temperature.

In these conditions curing will be extended and there is the possibility of amine bloom forming on the Intertherm 7050 surface that may adversely affect the adhesion of subsequent coatings. If an amine bloom is formed, it should be removed by solvent wipe.

Application

Application by moulding or casting is also recommended for Intertherm 7050. It may be dispensed into moulds, e.g. pipe half shells, using modified plural component application equipment. Please consult the Intertherm 7050 Application Manual for further information.

Maximum film build in one coat is best attained by plural component airless spray. When applying by trowel or other methods, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

Where high thicknesses are to be applied (typically over 1.6-2.0 inches (40-50 mm) depending on environmental conditions) the coating should be applied in two stages, allowing the first stage to cure before the second is applied. This is to prevent excessive heat building up due to the exothermic reaction that occurs during cure. For further advice please contact International Protective Coatings.

Equipment

Only equipment qualified by International Protective Coatings shall be used as detailed in the Intertherm 7050 Application Manual or by the International Protective Coatings Technical Service Representative.

Alternative Surface Preparation

International Protective Coatings procedures are also developed and available under certain project specific circumstances for wet blasting, needle gunning and ultra high pressure water blasting - Seek specific advice from International Paint Fire and Insulation Products.

Operating Notes

The maximum operating temperature for Intertherm 7050 is 248°F (120°C).

In common with all epoxies, Intertherm 7050 will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive or insulation performance.

Where a durable cosmetic finish or reduced surface spread of flame is required, overcoat with recommended topcoats.

Epoxy Wrap System

For severe service conditions requiring a more durable outer layer over the Intertherm 7050, International's flexible wrap system may be used. This system consists of a knitted glass tape of approximately 5 inches (127 mm) wide overlapped 50% and impregnated with a flexible epoxy resin.

Please consult the Intertherm 7050 Application Manual for further information.

D.F.T. Calculation

The required thickness of Intertherm 7050 is dependent on the design requirements and operating conditions of the structure requiring protection.

D.F.T. requirements for standard pipe sizes and common service conditions are available from published tables. For other applications, individual D.F.T. recommendations will be provided by International Protective Coatings.

Thermal Properties

Thermal Conductivity:	0.118 W/(m·K) at 20°C ASTM C177 (0.068 BTU/Ft·Hr·°F at 68°F)
	0.120 W/(m·K) at 60°C ASTM C177 (0.069 BTU/Ft·Hr·°F at 140°F)

Specific Heat: 1250 J/(kg·K) (0.299 BTU/(lb·°F))

SYSTEMS COMPATIBILITY

Intertherm 7050 may be applied directly to correctly prepared abrasive blasted substrates. Where a primer is used, the following are recommended:

Intertherm 228
Interplus 256

Intertherm 7050 is generally overcoated for identification purposes or to provide additional protection.

The following topcoats are recommended to provide a durable cosmetic finish:

Interfine 629HS
Interthane 990

Ideally, Intertherm 7050 should be overcoated once hard dry (see table on page 1 for guidance) and before the coating becomes contaminated.

For topcoats designed to reduce surface spread of flame or details of other approved primers/topcoats, please consult International Protective Coatings.

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Weight	Pack	Weight	Pack
	30 kg	10.7 kg	20 liter	8.6 kg	20 liter
¹ The unit is supplied as: 2 x 10.7 kg Part A in 20 litre containers; 1 x 8.6 kg Part B in a 20 litre container. For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
	30 kg	13.55 kg		11.8 kg	
STORAGE	Shelf Life	6 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Issue date: 2/13/2012

Copyright © AkzoNobel, 2/13/2012.

 Copyright © AkzoNobel, 2/13/2012.

www.international-pc.com