

## Polymer Modified Cementitious Flooring

### FORMERLY FLEXCRETE CEMPROTEC E-FLOOR

#### PRODUCT DESCRIPTION

A two component, water-based (VOC-free), epoxy and polymer modified cementitious coating for the protection of concrete floors. It exhibits a high degree of flow for easy application by pouring or pumping techniques to give a smooth surface finish. It cures to form a hardwearing, durable coating, offering low permeability to water and providing very high chemical and abrasion resistance to ensure long term protection.

#### INTENDED USES

Specifically designed for the protection of concrete floors and decks subject to trafficking in demanding internal and external environments. Intercrete 4851 can be reinforced with Intercrete 4872 tape to accommodate movement over construction joints.

Intercrete 4851 offers low permeability to water at 10 bar positive and negative pressure along with excellent resistance to oxygen and chloride ion diffusion.

CE-marked in accordance with BS EN 1504-2. Suitable for surface protection systems principles 2.2, 5.1, 6.1, 8.2 as defined in BS EN 1504-2.

#### PRACTICAL INFORMATION FOR INTERCRETE 4851

<b>Colour</b>	Grey			
<b>Volume Solids</b>	100%			
<b>Typical Thickness</b>	2 millimetres (80 mils) dry thickness			
<b>Practical Coverage</b>	On prepared substrates, a 30kg pack will cover approximately 8.1m <sup>2</sup> at 2mm thickness Practical coverage will depend upon the surface profile and porosity of the area being coated and appropriate losses must be taken into consideration			
<b>Method of Application</b>	Serrated Trowel, Skid Leveller, Float, Pin Leveller			
<b>Shelf Life</b>	12 months at 20°C (68°F).			
<b>Pack Size</b>	30kg composite packs			
<b>Working Pot Life</b>	20°C (68°F) 30 minutes			
<b>Drying Time</b>	Overcoating interval with self			
<b>Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<i>Minimum</i>	<i>Maximum</i>
20°C (68°F)	1.5 hours	4 hours	24 hours	Not applicable

#### COMPLIANCE AND CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Suitable for surface protection systems principles 2.2, 5.1, 6.1, 8.2 as defined in BS EN 1504-2.
- CE-marked in accordance with EN 13813 Class CT-C40-F10-AR1.
- Compliant with LU Standard 1-085 'Fire Safety Performance of Materials'.



## Protective Coatings

## Polymer Modified Cementitious Flooring

### SPECIFICATION CLAUSE

The protective coating to concrete floors shall be a two component epoxy and polymer modified cementitious coating, CE-marked in accordance with BS EN 1504-2, and shall comply with the following performance specification:

- Impermeable to water under 10 bar hydrostatic pressure
- Adhesive strength of at least 2MPa onto concrete in accordance with EN 1542.
- Can be applied to "green" concrete

### SURFACE PREPARATION

---

#### Concrete

The strength of the concrete sub-base should be a minimum of 20MPa. All surfaces should be clean, dry and free from curing compounds, release agents, trowelling compounds, surface hardeners, efflorescence, grease, oil, dirt, old coatings and loose or disintegrating concrete. Smooth surfaces should be roughened. This is best achieved using totally-enclosed shotblasting equipment, scarification, scabbling or grinding. The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without any standing water.

Areas still exhibiting signs of oil, grease, etc., must be treated with a proprietary degreaser. In instances of heavy contamination, it may be necessary to use hot compressed air equipment, flame spalling or steam cleaning techniques. All debris should be removed to leave a thoroughly clean, dust-free, open-textured surface.

#### Priming

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without any standing water. This includes Intercrete 4851 or any previous coats of Intercrete 4852. To prevent outgassing, the substrate should be sealed with Intercrete 4850, at a typical coverage rate of 5m<sup>2</sup>/litre. Allow to become transparent, typically 1-3 hours dependent on climatic conditions, before proceeding.

---

### APPLICATION

#### Mixing

Intercrete 4851 is supplied in two parts; a liquid component (Part A) and a powder component (Part B). MIX FULL UNITS ONLY. Shake Part A thoroughly and pour into a suitable mixing container, then slowly add Part B and mix for a minimum of 5 minutes until homogeneous, without any lumps. During the 5-minute mixing period, scrape the sides of the mixing container to prevent lumps forming. Mixing should be carried out using a slow-speed drill and paddle, designed to entrap as little air as possible. Once the unit has been mixed it should be used within the working pot life specified.

#### Skid Leveller

Recommended

#### Work Stoppages / Clean Up

Clean all equipment immediately after use with clean water.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

## Polymer Modified Cementitious Flooring

### PRODUCT CHARACTERISTICS

#### Joints

All formed joints in the existing floor or deck MUST be continued through into the new coating. Over construction joints and 'live' cracks, Intercrete 4851 should be reinforced with Intercrete 4872, using Intercrete 4840 as the embedment material (see separate technical data sheets for further information).

#### Placing

Intercrete 4851 should be poured or pumped onto the prepared surface and spread to a minimum thickness of 2mm with a squeegee or pin leveller. Roll the surface with a spiked roller to remove entrapped air and to ensure a dense finish. Care must be taken to ensure a minimum 2mm thickness is achieved. Where required, to enhance the skid and abrasion resistance of the finished Intercrete 4851, immediately broadcast a suitable aggregate into the surface, ensuring that the particles are distributed evenly without disrupting the smooth surface of the coating. Contact Protective Coatings Technical Department for further information. Allow to cure for a minimum of 4 hours before removing any excess aggregate, which may be sieved and re-used. Apply Intercrete 4870 with a roller at 5m<sup>2</sup>/litre. Finishing must be completed within the working life of the material and no later than 10 minutes after placing. Allow to cure for a minimum of 4 hours before subjecting the application to light foot traffic.

#### Curing

Normal procedures relating to curing of cementitious products should be strictly adhered to. The surface must be protected from strong sunlight, drying winds and high air movements, to prevent skinning during placing and rapid drying out in the plastic state. On unsanded finishes, the coating must be cured using Intercrete 4870, taking care to avoid overspray onto surfaces yet to be treated.

CE mark applies to products manufactured at Tomlinson Road, Leyland, PR25 2DY England, under reference 2797-CPR-530942.

---

### APPLICATION TIPS

- Keep the wet edge live with a steady supply of mixed material and regular spike rolling.
- Regularly clean and dry spiked rollers to avoid material build-up.
- Use spiked shoes during application to avoid disturbing the coating.
- Regularly check coating thickness during application using the wet film thickness gauge available from AkzoNobel.
- Care should be taken during application to ensure that air is not entrapped into the surface.
- Fresh material can be joined up to existing hardened material using a simple butt joint. Apply tape to the hardened material and apply fresh material up to it. Remove tape whilst wet to leave a neat edge.
- In cold, humid conditions, condensation may form on surfaces treated with Intercrete 4851, resulting in darkening of finish and retardation of set.
- Enhance adhesion of subsequent high build decorative/tiled finishes by broadcasting a suitable fine aggregate into the freshly laid material.
- Cure for a minimum of 72 hours before overcoating or applying tiled finishes.
- Apply Intercrete 4870 curing membrane as an even, fine mist spray. Do not over-apply or allow to pond on the surface or cracking may occur.
- When broadcasting aggregate, use techniques such that the particles are thrown upwards and fall evenly without disturbing the smooth surface of the coating. Use a grit blower on larger areas.
- Cold Weather Working (See separate Guide):  $\geq 3^{\circ}\text{C}$  (37°F) on a rising thermometer,  $\geq 5^{\circ}\text{C}$  (41°F) on a falling thermometer.
- Hot Weather Working (See separate Guide): Store material in cool conditions to maximise working life. Shade applied material from strong sunlight. Spray-apply a second coat of Intercrete 4870. If possible, avoid extreme temperatures by working at night.

## Polymer Modified Cementitious Flooring

### TECHNICAL DATA / MECHANICAL CHARACTERISTICS

Standard and Property	BS EN 1504-2 Requirement	Result
EN 12190 Compressive Strength	$\geq 50$ MPa (Class II)	28 days: 54MPa
BS4551 Compressive Strength Development at 20°C		4 hours 8.0MPa 1 day 18MPa 7 days 33.5MPa 28 days 55MPa
EN196-1 Flexural Strength		28 Days: $>12$ MPa
EN 1542 Adhesive Bond	$> 2.00$ MPa	3.36MPa
BS EN ISO 7783-2 Water Vapour Permeability (Equivalent Air Layer Thickness)	Class 1 $S_D = 5$ m	$S_D = 1.12$ m
EN13687-1 Thermal Compatibility	$> 2.00$ MPa	3.10MPa
Vinci Test: Water Permeability Coefficient (Equivalent Concrete Thickness)		$1.12 \times 10^{-16}$ m/sec 2mm = 2310mm of concrete
DIN 1048 Resistance to Water Pressure		10 bar (100m hydrostatic head) positive and negative)
EN13813 Wear Resistance		Exceeds AR0,5: Highest classification of wear resistance
EN 1062-3 Liquid Water Transmission Rate (Capillary Absorption and Permeability to Liquid water)	Class III (low) $w < 0.1 \text{ kg} \cdot \text{m}^{-2} \cdot \text{h}^{-0.5}$	$w = 0.073 \text{ kg} \cdot \text{m}^{-2} \cdot \text{h}^{-0.5}$
EN1770 Coefficient of Thermal Expansion	$< 30 \times 10^{-6} \text{ K}^{-1}$	$23.7 \times 10^{-6} \text{ K}^{-1}$
EN 13501-1 Reaction to Fire	Euroclass	Euroclass A2 <sub>FL</sub> – s1
ASTM C1202-12 Resistance to Chloride Ion Penetration		3659 Coulomb (control concrete) 12915 Coulomb)

**Note:** The properties given above are obtained from laboratory tests: results obtained from on-site testing may vary according to site conditions.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 12/04/2019.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

[www.international-pc.com](http://www.international-pc.com)