

Bimodal Polymer

PRODUCT DESCRIPTION

A patented, two component, high performance chemical tank lining with low absorption and easy clean characteristics requiring heated post cure.

INTENDED USES

To provide corrosion protection for the internals of carbon steel and stainless steel chemical tanks, vessels and containers.

Suitable for the carriage of an extensive range of aggressive cargos including but not limited to solvents, chemicals, petrochemicals and acids whether concentrated, diluted or spent.

Interline 9001 offers excellent resistance to a wide range of chemicals making it suitable for tanks that may be used for different chemical cargos or single specification for a wide range of chemical tanks. Cross-contamination due to cargo sequencing is reduced due to the ultra-low absorption of the Interline 9001. The smooth and high gloss finish of Interline 9001 makes it easier to clean, reducing cleaning costs.

PRACTICAL INFORMATION FOR INTERLINE 9001

Color	Buff, Gray, Red
Gloss Level	Gloss
Volume Solids	80%
Typical Thickness	4-8 mils (100-200 microns) dry equivalent to 5-10 mils (125-250 microns) wet
Theoretical Coverage	214 sq.ft/US gallon at 6 mils d.f.t and stated volume solids 5.33 m ² /liter at 150 microns d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless spray, Conventional Spray, Brush, Roller

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
59°F (15°C)	32 hours	40 hours	48 hours	5 days
77°F (25°C)	14 hours	18 hours	24 hours	4 days
95°F (35°C)	6 hours	9 hours	16 hours	3 days

REGULATORY DATA **Flash Point (Typical)** Part A 93°F (34°C); Part B 212°F (100°C); Mixed 115°F (46°C)

VOC 1.47 lb/gal (177 g/lit) EPA Method 24
93 g/kg EU Solvent Emissions Directive
(Council Directive 1999/13/EC)
115 g/lit Chinese National Standard GB23985

See Product Characteristics section for further details

Protective Coatings

Bimodal Polymer

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Where necessary, remove weld spatter, and smooth weld seams and sharp edges. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2.5 (ISO 8501-1:2007) or SSPC-SP10. For aqueous cargoes in elevated temperature service, the minimum standard of surface preparation should be abrasive blast clean to SSPC-SP5 or Sa3 (ISO 8501-1:2007). A sharp, angular surface profile of 2-3 mils (50-75 microns) is required.

The preferred method of holding the blast standard is by dehumidification. Interline 9001 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidized area should be reblasted to the standard specified above. Surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner.

Areas of breakdown, damage, weld seam etc. should be prepared to the specified standards (e.g. SSPC-SP10 or Sa2½ (ISO8501-1: 2007) or power tool cleaned to SSPC-SP11 or Pt3 (JRSA SPSS:1984)).

APPLICATION

Mixing	<p>Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed, it must be used within the working pot life specified.</p> <p>(1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.</p> <p>Mixed unit must be maintained at >68°F (20°C) during mixing and application.</p> <p>It is recommended that Interline 9001 is allowed a 15 minute induction period after mixing, prior to commencing application.</p>	
Mix Ratio	7.52part(s):1part(s) by volume	
Working Pot Life	77°F (25°C) 60 minutes	95°F (35°C) 60 minutes
Airless Spray	Recommended	Tip Range 15-23 thou (0.38-0.58 mm) Total output fluid pressure at spray tip not less than 2503 psi (176 kg/cm ²)
Air Spray (Conventional)	Suitable	
Brush	Suitable - Small areas and stripe coating only	Multiple coats may be required to achieve specified film thickness.
Roller	Suitable - Small areas and stripe coating only	Multiple coats may be required to achieve specified film thickness.
Thinner	DO NOT THIN	
Cleaner	International GTA415 / GTA822	
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822 or International GTA415. Once units of paint have been mixed, they should not be resealed and it is advised that after prolonged stoppages, work recommences with freshly mixed units.	
Clean Up	Clean all equipment immediately after use with International GTA822 or International GTA415. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency should depend upon amount sprayed, temperature and elapsed time, including any delays.	
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Bimodal Polymer

PRODUCT CHARACTERISTICS

The detailed Interline 9001 Application Guidelines should be consulted prior to use.

International Protective Coatings should be consulted to confirm that Interline 9001 is suitable for the range of chemicals to be stored. For storage of certain chemicals, a mandatory heated post-cure is required.

Apply in good climatic conditions. The temperature of the surface to be coated must be at least 5°F (3° C) above the dew point. When applying Interline 9001 in confined spaces, ensure adequate ventilation. A mandatory heated post-cure is required before the coating enters service; consult International Protective Coatings for further information.

Interline 9001 will not cure adequately below 59°F (15°F). At no time during the application and up to the first 48 hours after application of the final coat must the steel temperature fall below 59°F (15°C) and the relative humidity exceed 50%.

Film Thickness:

The minimum required DFT is 9.6 mils (240µm), the maximum DFT is 18 mils (450µm).

In way of areas of tanks that are difficult to paint due to their configuration , e.g heavily stiffened tanks, and where a degree of overthickness is unavoidable, a maximum of 24 mils (600 microns) dft is acceptable.

The drying times and overcoating intervals may alter due to various on-site factors such as tank configuration, ventilation rates etc.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

Interline 9001 will normally be applied direct to metal and is not normally overcoated with any product other than itself.

Bimodal Polymer

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 liter	17.65 liter	20 liter	2.35 liter	2.5 liter
	5 liter	4.41 liter	5 liter	0.59 liter	1 liter
	1 US gal	0.88 US gal	1 US gal	0.12 US gal	1 US quart

For availability of other pack sizes contact International Protective Coatings

SHIPPING WEIGHT (TYPICAL)	Unit Size	Weight
	5 liter	8.83 kg
	20 liter	32.3 kg
	1 US gal	15.9 lb

STORAGE	Shelf Life	12 months at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	--

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 4/10/2018.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com