

## Polyurethane

### PRODUCT DESCRIPTION

A two component solvent borne, high solids aliphatic acrylic polyurethane topcoat with optimised application properties and superior aesthetics. Interthane 990E is ideal for use wherever a durable and visually appealing finish is required.

### INTENDED USES

Interthane 990E is ideal for use in newconstruction or maintenance projects in a wide variety of environments for both industrial and commercial projects, from manufacturing and infrastructure to power generation and a wide variety of oil and gas assets. Contributing to the performance of an anti-corrosion system, Interthane 990E can be applied over a suitable primer, intermediate or passive fire protection system to provide excellent functionality and appearance with high gloss and low VOC content.

### PRACTICAL INFORMATION FOR INTERTHANE 990E

|                              |   |
|------------------------------|---|
| <b>Colour</b>                | Wide range via the Chromascan system  |
| <b>Gloss Level</b>           | High Gloss  |
| <b>Volume Solids</b>         | 70% ± 3%  |
| <b>Typical Thickness</b>     | 50-75 microns (2-3 mils) dry equivalent to<br>71-107 microns (2.8-4.3 mils) wet   |
| <b>Theoretical Coverage</b>  | 14 m <sup>2</sup> /litre at 50 microns d.f.t and stated volume solids<br>561 sq.ft/US gallon at 2 mils d.f.t and stated volume solids |
| <b>Practical Coverage</b>    | Allow appropriate loss factors  |
| <b>Method of Application</b> | Airless Spray, Air Spray, Brush, Roller   |
| <b>Drying Time</b>           |   |

| Temperature  | Touch Dry  | Hard Dry | Overcoating Interval with recommended topcoats |                       |
|--------------|------------|----------|--|-----------------------|
|              |            |          | Minimum  | Maximum               |
| -5°C (23°F)  | 22 hours   | 68 hours | 60 hours                                       | Extended <sup>1</sup> |
| 5°C (41°F)   | 5 hours    | 24 hours | 21 hours                                       | Extended <sup>1</sup> |
| 15°C (59°F)  | 30 minutes | 10 hours | 10 hours                                       | Extended <sup>1</sup> |
| 25°C (77°F)  | 15 minutes | 6 hours  | 6 hours  | Extended <sup>1</sup> |
| 40°C (104°F) | 15 minutes | 4 hours  | 4 hours  | Extended <sup>1</sup> |

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

### REGULATORY DATA

|                              |  |   |  |
|------------------------------|--|---|--|
| <b>Flash Point (Typical)</b> | Part A 26°C (79°F); Part B 49°C (120°F); Mixed 29°C (84°F) |   |  |
| <b>Product Weight</b>        | 1.49 kg/l (12.4 lb/gal)                                    |   |  |
| <b>VOC</b>                   | 2.58 lb/gal (310 g/l)                                      | EPA Method 24   |  |
|                              | 207 g/kg   | EU Solvent Emissions Directive (Council Directive 2010/75/EU) |  |
|                              | 284 g/l  | Chinese National Standard GB23985                             |  |
|                              | 325 g/l as supplied under Korea Clean Air Conservation Act |   |  |

See Product Characteristics section for further details

## Protective Coatings

## Polyurethane

### SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

#### Primed Surfaces

Interthane 990E should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Interthane 990E must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Interthane 990E.

### APPLICATION

|                                 |   |  |   |                          |
|---------------------------------|---|--|---|--------------------------|
| <b>Mixing</b>                   | Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.   |  |   |                          |
|                                 | (1) Agitate Base (Part A) with a power agitator.  |  |   |                          |
|                                 | (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.   |  |   |                          |
| <b>Mix Ratio</b>                | 8 part(s) : 1 part(s) by volume   |  |   |                          |
| <b>Working Pot Life</b>         | -5°C (23°F)<br>3 hours  | 5°C (41°F)<br>2.5 hours  | 15°C (59°F)<br>2 hours                  | 25°C (77°F)<br>1.5 hours |
| <b>Airless Spray</b>            | Recommended   | Tip Range 0.33-0.45 mm (13-18 thou)<br>Total output fluid pressure at spray tip not less than 155 kg/cm <sup>2</sup> (2204 p.s.i.) |   |                          |
| <b>Air Spray (Pressure Pot)</b> | Recommended   | Gun<br>Air Cap<br>Fluid Tip  | DeVilbiss MBC or JGA<br>704 or 765<br>E |                          |
| <b>Air Spray (Conventional)</b> | Recommended   | Use suitable proprietary equipment   |   |                          |
| <b>Brush</b>                    | Suitable  | Typically 40-50 microns (1.6-2.0 mils) can be achieved   |   |                          |
| <b>Roller</b>                   | Suitable  | Typically 40-50 microns (1.6-2.0 mils) can be achieved   |   |                          |
| <b>Thinner</b>                  | International GTA713 (or Do not thin more than allowed by local International GTA733 or environmental legislation GTA056)   |  |   |                          |
| <b>Cleaner</b>                  | International GTA713 (or International GTA733)  |  |   |                          |
| <b>Work Stoppages</b>           | Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA713. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.     |  |   |                          |
| <b>Clean Up</b>                 | Clean all equipment immediately after use with International GTA713. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. |  |   |                          |
|                                 | All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.   |  |   |                          |

## Polyurethane

### PRODUCT CHARACTERISTICS

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible.

Best results in terms of gloss and appearance will always be obtained by conventional air spray application.

For brush and roller application, and in some colours, two coats of Interthane 990E may be required to give uniform coverage, especially when applying Interthane 990E over dark undercoats, and when using certain lead free bright colours such as yellows and oranges. Best practice is to use a colour compatible intermediate or anticorrosive coating under the Interthane 990E.

When overcoating after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as oil, grease, salt crystals and traffic fumes, before application of a further coat of Interthane 990E.

Absolute measured adhesion of topcoats to aged Interthane 990E is less than that to fresh material, however, it is adequate for the specified end use.

This product must only be thinned using the recommended International thinners. The use of alternative thinners, particularly those containing alcohols, can severely affect the curing mechanism of the coating.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

When applying Interthane 990E in confined spaces ensure adequate ventilation.

Interthane 990E is capable of curing at temperatures below 0°C (32°F). However, this product should not be applied at temperatures below 0°C (32°F) where there is a possibility of ice formation on the substrate. Condensation occurring during or immediately after application may result in a matt finish and an inferior film. Premature exposure to ponding water will cause colour change, especially in dark colours and at low temperatures.

This product is not recommended for use in immersion conditions. When severe chemical or solvent splashing is likely to occur contact International Protective Coatings for information regarding suitability.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

---

### SYSTEMS COMPATIBILITY

The following primers/intermediates are recommended for Interthane 990E:

|                 |                 |                     |
|-----------------|-----------------|---------------------|
| Chartek 8E      | Intercure 200HS | Interseal 1052      |
| Chartek 1709    | Intergard 251HS | Intershield 300     |
| Interchar 1190  | Intergard 2511* | Intershield 4000USP |
| Interchar 2060  | Intergard 269   | Interzone 954       |
| Interchar 1260  | Intergard 345   | Interzone 954GF     |
| Interchar 1290  | Intergard 475HS |                     |
| Interchar 3120* | Interseal 670HS |                     |

\*available only in selected countries.

For other suitable primers/intermediates consult International Protective Coatings.

Interthane 990E is designed only to be topcoated with itself.

## Polyurethane

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult AkzoNobel for further advice.

**Warning: Contains isocyanate. Wear air-fed hood for spray application.**

| PACK SIZE | Unit Size | Part A      |          | Part B     |         |
|-----------|-----------|-------------|----------|------------|---------|
|           |           | Vol         | Pack     | Vol        | Pack    |
|           | 20 litre  | 17.78 litre | 20 litre | 2.22 litre | 5 litre |
|           | 5 litre   | 4.45 litre  | 5 litre  | 0.55 litre | 1 litre |

For availability of other pack sizes, contact AkzoNobel.

| SHIPPING WEIGHT (TYPICAL) | Unit Size | Part A  | Part B  |
|---------------------------|-----------|---------|---------|
|                           | 20 litre  | 27.2 kg | 2.36 kg |
|                           | 5 litre   | 7.31 kg | 0.7 kg  |

| STORAGE | Shelf Life   |
|---------|--|
|         | 12 months at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. |

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 06/07/2022.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

**[www.international-pc.com](http://www.international-pc.com)**