

## Rapid Setting Repair Mortar

**PRODUCT DESCRIPTION**

Supplied as a single component, fibre reinforced, fast setting cement based repair mortar.  
Requires the addition of clean water at site.

**INTENDED USES**

Specifically designed for the structural repair of concrete structures such as runways, bridges, decks and floors, which cannot be taken out of service for prolonged periods.

Intercrete 4802 exhibits a combination of curing at low temperatures, complete compatibility with concrete and consistent strength development making it the ideal choice where rapid return to service is required.

This product can be used for repairs up to 100mm (4 inches) deep as supplied. For deeper repairs of up to 300mm (12 inches) Intercrete 4802 can be combined with a non-porous aggregate of particle size 6-10mm (0.24-0.39 inches) e.g. granite to form a pourable concrete.

**PRACTICAL INFORMATION FOR INTERCRETE 4802**

<b>Colour</b>	Grey			
<b>Gloss Level</b>	Matt			
<b>Volume Solids</b>	100%			
<b>Typical Thickness</b>	5mm - 100mm (0.2 - 4 inches) dry			
<b>Theoretical Coverage</b>	Typically 1.33m <sup>2</sup> at 10mm (0.39 inches) dry film thickness per 25kg supplied			
<b>Practical Coverage</b>	Allow appropriate loss factors			
<b>Density</b>	2150 kg/m <sup>3</sup> (134.218 lb/ft <sup>3</sup> )			
<b>Method of Application</b>	Float, Hand Moulding, Trowel			
<b>Drying Time</b>	Overcoating interval with self			
<b>Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	<i>Minimum</i>	<i>Maximum</i>
20°C (68°F)	15 minutes	60 minutes	20 minutes	7 days <sup>1</sup>

<sup>1</sup> If the maximum overcoating interval is exceeded the surface must be thoroughly cleaned and saturated prior to overcoating.

**REGULATORY DATA**

<b>Flash Point (Typical)</b>	Not applicable		
<b>VOC</b>	0 g/lit	Calculated	
See Product Characteristics section for further details			

## Protective Coatings

## Rapid Setting Repair Mortar

### SURFACE PREPARATION

#### Concrete Substrates

Mechanically remove all damaged concrete back to sound, intact material. It is recommended that any steel reinforcement present be exposed to at least 25mm (1 inch) behind the bars and 50mm (2 inches) beyond the point at which corrosion is visible.

The perimeter of the repair area should be stepped to a depth of 10mm (0.4 inches) using a saw, disc or power chisel. Feather edges must be avoided. Smooth surfaces should be roughened.

All surfaces should be clean and free from laitance, curing compounds, release agents, efflorescence, grease, oil, dirt, old coatings and loose or disintegrating concrete. The preferred methods of surface preparation are wet grit or water blasting techniques.

Any steel reinforcement present will require appropriate treatment using Intercrete 4871; consult that product datasheet for further information.

Thoroughly soak the substrate with clean water until fully saturated. Remove excess water prior to application of Intercrete 4802.

The compressive strength of the concrete substrate should be a minimum of 20MPa.

### APPLICATION

<b>Mixing</b>	Intercrete 4802 is supplied as a single component powder. Pour 3.5 litres of clean water into a mixing vessel then add one 25kg bag of Intercrete 4802. Mix using a slow speed drill and paddle with a maximum speed of 750rpm. Mix for 2-3 minutes to an even consistency. For larger repairs up to 100mm deep, Intercrete 4802 may be extended by the addition of up to 50% sharp sand. For deck repairs up to a maximum depth of 300mm, up to 100% 6-10mm aggregate may be added with a small addition of water, up to 1 litre, to produce a semi-flowing mortar consistency. <b>Do not use a concrete mixer</b>
<b>Mix Ratio</b>	For part mixing, use 5.5 part(s) Intercrete 4802: 1 part(s) Clean Water by volume
<b>Working Pot Life</b>	20°C (68°F) 15 minutes
	<p><b>Intercrete 4802 Application</b></p> <p><b>Float</b> - recommended</p> <p><b>Hand Moulding</b> - recommended</p> <p><b>Trowel</b> - recommended</p>
<b>Thinner</b>	<b>DO NOT THIN</b>
<b>Cleaner</b>	Clean Water
<b>Work Stoppages</b>	Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.
<b>Clean Up</b>	Clean all equipment immediately after use with clean water.
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

## Rapid Setting Repair Mortar

### PRODUCT CHARACTERISTICS

Always consult the Intercrete 4802 Application Guidelines prior to use.

**This datasheet provides general guidance on the use of Intercrete 4802. Specific project requirements will be dependent upon the substrate condition, service end use and environmental conditions. Always consult International Protective Coatings to confirm that Intercrete 4802 is suitable for the intended end use.**

**The detailed project specification provided by International Protective Coatings must be followed at all times.**

This product will not cure adequately below 5°C (41°F). For maximum performance, curing temperatures should be between 10°C (50°F) and 35°C (95°F).

In order to reduce waste due to the short working pot life, best practice is to mix sufficient material to repair 1m<sup>2</sup> at a time.

It is important that the surface of Intercrete 4802 is protected from strong sunlight and drying winds. To aid curing, Intercrete 4870 curing membrane should be applied directly over Intercrete 4802. Alternatively, polythene sheeting can be used.

### Mechanical Characteristics

(typical values)

Compressive Strength (BS4551 @ 20°C (68°F))

1 hour 10MPa  
2 hours 20MPa  
4 hours 30MPa  
1 day 40MPa  
7 days 50MPa  
28 days 60MPa

Flexural Strength (BS4551 @ 20°C (68°F))

28 days 10.5MPa

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

### SYSTEMS COMPATIBILITY

Depending upon the condition of the substrate and any exposed steel reinforcement, additional surface preparation products from the Intercrete range may be required prior to the application of Intercrete 4802. Consult International Protective Coatings for further details.

The following topcoats are recommended for Intercrete 4802:

Intercrete 4850  
Intercrete 4802  
Intercrete 4870

## Rapid Setting Repair Mortar

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Intercrete 4802 Application Guidelines

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

### PACK SIZE

25kg packs  
For availability of other pack sizes, contact International Protective Coatings.

### SHIPPING WEIGHT (TYPICAL)

### STORAGE

Shelf Life                      12 months minimum at 25°C (77°F).

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

**[www.international-pc.com](http://www.international-pc.com)**