

Modified Acrylic

PRODUCT DESCRIPTION A single component, fast drying, modified acrylic finish.

INTENDED USES To be used in atmospheric environments for Power and Oil and Gas downstream projects.

PRACTICAL INFORMATION FOR INTERSHEEN 7579

Colour	Range of colours via the Chromascan system
Gloss Level	Semi Gloss
Volume Solids	54% ±2% (ISO 3233:1998)
Typical Thickness	50-75 microns (2-3 mils) dry equivalent to 93-139 microns (3.7-5.6 mils) wet
Theoretical Coverage	10.80 m ² /litre at 50 microns d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless Spray, Brush, Roller
Drying Time	

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
-5°C (23°F)	2 hours	36 hours	24 hours	Extended ¹
5°C (41°F)	60 minutes	24 hours	8 hours	Extended ¹
25°C (77°F)	30 minutes	8 hours	4 hours	Extended ¹
35°C (95°F)	15 minutes	8 hours	2 hours	Extended ¹

¹ See International Protective Coatings Definitions and Abbreviations

REGULATORY DATA

Flash Point (Typical)	29°C (84°F)	
Product Weight	1.399 kg/l (11.7 lb/gal)	
VOC	3.40 lb/gal (408 g/l)	EPA Method 24
	298 g/kg	EU Solvent Emissions Directive (Council Directive 2010/75/EU)
	405 g/l	Chinese National Standard GB23985

See Product Characteristics section for further details

Modified Acrylic

SURFACE PREPARATION

All surfaces to be coated should be clean and free from contamination. Prior to application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Primed Surfaces

Intersheen 7579 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Intersheen 7579 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Intersheen 7579.

APPLICATION

Mixing	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.	
Airless Spray	Recommended	Tip Range 0.38-0.53 mm (15-21 thou)
Brush	Recommended - Small areas only	Multiple coats may be required to achieve specified film thickness.
Roller	Recommended - Small areas only	Multiple coats may be required to achieve specified film thickness.
Thinner Cleaner	Not normally required. If necessary, use International GTA007.	
Work Stoppages	Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage.	
Clean Up	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.	
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

Modified Acrylic

PRODUCT CHARACTERISTICS

Apply in good climatic conditions. The temperature of the surface to be coated must be at least 3°C (5°F) above the dew point.

Ensure adequate ventilation is provided throughout application and curing.

Intersheen 7579 should be protected from pooling or running water, condensation/high humidity and chemical attack at all times.

Condensation occurring during or immediately after application may result in a matt finish and an inferior film.

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible.

When applying Intersheen 7579 by brush or roller, care is required to prevent "pick-up" of recently applied one pack coatings.

Some shades may require more than one coat to achieve full opacity and uniform appearance.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

The following primers are approved for use with Intersheen 7579:

Interprime 198

For other suitable primers, consult International Protective Coatings.

Modified Acrylic

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult AkzoNobel for further advice.

PACK SIZE	Unit Size	Vol	Pack
	20 litre	20 litre	20 litre

SHIPPING WEIGHT (TYPICAL)	Unit Size	
	20 litre	29.5 kg

STORAGE	Shelf Life	
	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 24/05/2023.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com