

Interprime® 1018



Akyd

PRODUCT DESCRIPTION

A one component, fast drying, high performance, universal alkyd primer.

INTENDED USES

Suitable for use in construction and for prefabricating building components, purlins and other sections.

Quick drying properties make it equally suitable for use at new construction in the fabrication shop.

PRACTICAL INFORMATION FOR INTERPRIME 1018

Colour	Grey, Red Oxide
Gloss Level	Matt
Volume Solids	40%
Typical Thickness	25-35 microns (1-1.4 mils) dry equivalent to 63-88 microns (2.5-3.5 mils) wet
Theoretical Coverage	16 m²/litre at 25 microns d.f.t and stated volume solids 642 sq.ft/US gallon at 1 mils d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Roller, Brush, Conventional Spray

Drying Time

Overcoating Interval with recommended topcoats

Temperature	Touch Dry	Hard Dry	Minimum	Maximum
25°C (77°F)	6 minutes	12 hours	10 hours	Extended
40°C (104°F)	5 minutes	8 hours	8 hours	Extended

REGULATORY DATA

Flash Point (Typical)	Part A 30°C (86°F)
Product Weight	1.29 kg/l (10.8 lb/gal)
VOC	529 g/lt Calculated

See Product Characteristics section for further details

Protective Coatings

Alkyd

SURFACE PREPARATION

The performance of this product will depend upon the degree of surface preparation. The surface to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Interprime 1018 is suitable for application to blast cleaned surfaces which were initially to the above standard but have been allowed to deteriorate under good shop conditions for up to 7-10 days. The surface may deteriorate to Sa2 standard but must be free from loose powdery deposits.

Maintenance and Site Touch-up

The product is designed for application to surfaces prepared to St2 (ISO 8501-1:2007) or SSPC-SP2. When using power tools care should be taken to avoid surface polishing. The product may also be applied to surfaces which have been brush blasted to Sa1 (ISO 8501-1:2007) or SSPC-SP7. On poor surfaces brush application will assist performance.

APPLICATION	Mixing	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.				
	Mix Ratio	Not applicable				
	Air Spray (Conventional)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E		
	Brush	Suitable	Typically 20-25 microns (0.8-1.0 mils) can be achieved			
	Roller	Suitable	Typically 20-25 microns (0.8-1.0 mils) can be achieved			
	Thinner	International GTA007	Do not thin more than allowed by local environmental legislation			
	Cleaner	International GTA007				
	Work Stoppages	Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.				
	Clean Up	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.				
		All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.				

Interprime® 1018



Alkyd

PRODUCT CHARACTERISTICS

Anti-corrosive performance on hand prepared steel is related directly to both the degree of surface preparation and the dry film thickness of the system applied.

When overcoating after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as oil, grease, salt crystals and traffic fumes.

This product must only be thinned using the recommended International thinners.

Do not apply at steel temperatures below 5°C (41°F).

When applying Interprime 1018 in confined spaces ensure adequate ventilation.

This product is not intended for use in aggressive, corrosive environments, or on heavily pitted or contaminated steel.

This product is not recommended for use in immersion conditions. When severe chemical or solvent splashing is likely to occur contact International Protective Coatings for information regarding suitability.

Care should be taken to avoid over-application of Interprime 1018 as cure and subsequent performance may be affected.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

The following topcoats are recommended for Interprime 1018:

Interlac 665
Interlac 1017

For other suitable topcoats, consult International Protective Coatings.

Alkyd

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
	20 litre	20 litre	20 litre
	5 litre	5 litre	5 litre
For availability of other pack sizes, contact International Protective Coatings.			
SHIPPING WEIGHT (TYPICAL)	Unit Size		
	20 litre	27.6 kg	
	5 litre	6.75 kg	
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com