

Alkyd

PRODUCT DESCRIPTION A single component alkyd gloss enamel finish.

INTENDED USES Maintenance coating for use in a wide range of industrial environments including offshore, petrochemical and chemical plants. Suitable for areas of limited chemical exposure where an economical single pack finish coat is required. As a cosmetic finish coat for alkyd based systems intended for both interior and exterior exposure.

PRACTICAL INFORMATION FOR INTERLAC 1017

| | |
|------------------------------|--|
| Colour | Range |
| Gloss Level | Gloss |
| Volume Solids | 36% |
| Typical Thickness | 35-45 microns (1.4-1.8 mils) dry equivalent to 97-125 microns (3.9-5 mils) wet |
| Theoretical Coverage | 9 m ² /litre at 40 microns d.f.t and stated volume solids 361 sq.ft/US gallon at 1.6 mils d.f.t and stated volume solids |
| Practical Coverage | Allow appropriate loss factors |
| Method of Application | Air Spray, Airless Spray, Brush, Roller |

Drying Time

| Temperature | Touch Dry | Hard Dry | Overcoating Interval with recommended topcoats | |
|--------------|-----------|----------|--|-----------------------|
| | | | Minimum | Maximum |
| 25°C (77°F) | 4 hours | 18 hours | 24 hours | Extended ¹ |
| 40°C (104°F) | 3 hours | 14 hours | 16 hours | Extended ¹ |

¹ See International Protective Coatings Definitions and Abbreviations

REGULATORY DATA

| | | |
|------------------------------|-----------------------|------------|
| Flash Point (Typical) | Part A 36°C (97°F) | |
| Product Weight | 1.1 kg/l (9.2 lb/gal) | |
| VOC | 554 g/lit | Calculated |

See Product Characteristics section for further details

Alkyd

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Primed Surfaces

Interlac 1017 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and Interlac 1017 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Interlac 1017.

APPLICATION

| | | | |
|---------------------------------|--|--|--------------------------------------|
| Mixing | This material is a one component coating and should always be mixed thoroughly with a power agitator before application. | | |
| Mix Ratio | Not applicable | | |
| Airless Spray | Recommended | Tip Range 0.33-0.48 mm (13-19 thou) Total output fluid pressure at spray tip not less than 141 kg/cm ² (2005 p.s.i.) | |
| Air Spray (Pressure Pot) | Recommended | Gun Air Cap Fluid Tip | DeVilbiss MBC or JGA Air Cap E |
| Brush | Recommended | Typically 25-40 microns (1.0-1.6 mils) can be achieved | |
| Roller | Recommended | Typically 25 microns (1.0 mils) can be achieved | |
| Thinner | International GTA004 | Do not thin more than allowed by local environmental legislation | |
| Cleaner | International GTA004 | | |
| Work Stoppages | Thoroughly flush all equipment with International GTA004. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use. | | |
| Clean Up | Clean all equipment immediately after use with GTA004. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. | | |

Alkyd

PRODUCT CHARACTERISTICS

Interlac 1017 is designed primarily for site application. Airless spray application at factory can easily lead to over-application with slow through drying and difficulty in handling. Over-application can also cause wrinkling on overcoating after ageing. Alternative alkyd finishes are available which are more suitable for factory use. Contact International Protective Coatings for information on these products.

Level of sheen and surface finish are dependent on application method. Avoid using a mixture of application methods whenever possible.

As with all alkyd systems, Interlac 1017 has limited chemical and solvent resistance and is not suitable for use in immersion situations or in conditions of continuous condensation.

Interlac 1017 is not designed for application over epoxies or polyurethanes, and should not be applied over zinc based primers because of dangers of saponification of the alkyd resin and consequent adhesion loss.

For brush and roller application, and in some colours, two coats of Interlac 1017 may be required to give uniform coverage.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

Interlac 1017 is only suitable for application over alkyd or oleoresinous priming systems, e.g.:

Interprime 198
Interprime 1018

For other suitable primers, consult International Protective Coatings.

Alkyd

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

| PACK SIZE | Unit Size | | |
|--|------------|--|----------|
| | | Vol | Pack |
| | 5 litre | 5 litre | 5 litre |
| | 20 litre | 20 litre | 20 litre |
| For availability of other pack sizes, contact International Protective Coatings. | | | |
| SHIPPING WEIGHT (TYPICAL) | Unit Size | | |
| | 20 litre | 26.5 kg | |
| | 5 litre | 6.5 kg | |
| STORAGE | Shelf Life | 12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. | |

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 05/02/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com